



<b>Sales Agent:</b> ArcelorMittal Int. North America 1 South Dearborn, 13th floor CHICAGO IL 60603 USA		<b>ArcelorMittal Belval &amp; Differdange</b> Service Gestion Qualité 66, rue de Luxembourg L-4009 Esch/Alzette		 ArcelorMittal
<b>Plant:</b> ArcelorMittal Belval & Differdange Site de Differdange L-4503 Differdange , LUXEMBOURG		<b>Certificate Nr X4029872</b> Delivery note number 4029872 from 10 July 2019		
Our reference : 1700028493		PLESA ANAHUAC Y CIAS S.A. DE C.V. AV. VALLE DE LAS ALAMEDAS 66-0 54940 COL. SAN FRANCISCO CHILPAN - TU MEXICO		
Your reference : 28499				
13.06.2019				
PLESA ANAHUAC Y CIAS S.A. DE C.V.				
ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED HOT ROLLED AMERICAN WIDE FLANGE BEAMS				
Manufacturer's test certificate acc. to ASTM A 6				

Ord.item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars
000001	W 12 X 12 X 87	40' 12.192 mm	3,146 kg	84405	3,146 kg		2
000002	W 12 X 12 X 96	40' 12.192 mm	3,486 kg	84558	3,486 kg		2

Heat nr	Heat analysis (%)																
	C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	Ti	CEV	Sn	Nb+V	
	<b>Min</b>	0,50			0,10												
	<b>Max</b>	0,23	1,60	0,035	0,045	0,40	0,60	0,45	0,35	0,150	0,050	0,150		0,45		0,150	
84405		0,07	0,76	0,029	0,030	0,18	0,009	0,38	0,17	0,12	0,007	0,008	0,050	0,001	0,27	0,03	0,015
84558		0,07	0,74	0,018	0,024	0,15	0,010	0,31	0,15	0,10	0,005	0,006	0,040	0,001	0,25	0,03	0,011

Heat nr	Tensile test				
	PSI	PSI 200 mm			
	Ys	UTS	El. (%)	Y/U	
	<b>Min</b>	50.000	65.000	18,00	
	<b>Max</b>	65.000		0,85	
84405		62.640	75.835	23,74	0,83
84405		63.220	76.560	23,98	0,83
84558		59.015	73.080	24,34	0,81
84558		59.595	73.805	24,59	0,81

Material melted and manufactured in LUXEMBOURG

Klecker Roberto  
 Porteur de signature spéciale  
  
 ArcelorMittal Belval & Differdange