

**WEIGHT MEMO-PACKING LIST**

**Nr. 2000888343**



ArcelorMittal

**ArcelorMittal Commercial Sections S.A.**

66, rue de Luxembourg, L-4221 Esch-sur-Alzette  
R.C. Luxembourg Section B 36.177

Contract nr.: 29890  
Works nr.: 1700029883  
Invoice nr.: 2000888343  
5 October 2020


Plesa Anahuac Y Cias, S.A. de C.V.  
Av. Valle de las Alamedas 66-O  
54940 COL. S. FRANCISCO CHILPAN, TULTITLA  
MEXICO

Port of loading: ANTWERPEN, Luxembourg  
Port of discharge: VERACRUZ  
Vessel name: PRT ACE

**SHIPPING MARKS**

Colour marking 1 On each bar At the end 1 stroke In red By indelible colour  
Standard label 1 label At 1 end At each bundle Order nr. Customer's name Size and length Quality and heat nr. Port of destination  
Country of origin

<u>Product</u>	<u>ID Bar.</u>	<u>Heat nr.</u>	<u>Number of</u>	<u>Number</u>	<u>Net weight</u>	<u>Gross weight</u>
<u>Size</u>			<u>bundles</u>	<u>bars</u>	<u>KG</u>	<u>KG</u>
<u>Length</u>						
Amer.wide fl. beams	A132775457	11250	1	4	4.877	4.877
W 16 X 10.25 X 67	A132775459	11250	1	4	4.877	4.877
40'	A132775461	11250	1	4	4.877	4.877
	A132775463	01249	1	4	4.877	4.877
	A132775467	01249	1	4	4.877	4.877
	A132775596	10724	1	4	4.877	4.877
	A132775595	10724	1	4	4.877	4.877
	A132775597	10724	1	2	2.438	2.438
Invoice item Totals			8	30	36.577	36.577
Invoice totals			8	30	36.577	36.577

<b>Sales Agent:</b> ArcelorMittal Int. North America 1 South Dearborn, 13th floor CHICAGO IL 60603 USA	<b>ArcelorMittal Belval &amp; Differdange</b> Service Gestion Qualité 66, rue de Luxembourg L-4009 Esch/Alzette	
<b>Plant:</b> ArcelorMittal Belval & Differdange Site de Belval L-4008 Esch/Alzette, LUXEMBOURG	<b>Certificate Nr X4243621</b> Delivery note number 4243621 from 26 August 2020	
Our reference : 1700029883 Your reference : 29890 03.07.2020 PLESA ANAHUAC Y CIAS S.A. DE C.V.	PLESA ANAHUAC Y CIAS S.A. DE C.V. AV. VALLE DE LAS ALAMEDAS 66-O 54940 COL. SAN FRANCISCO CHILPAN - TU MEXICO	
ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED HOT ROLLED AMERICAN WIDE FLANGE BEAMS		
Manufacturer's test certificate acc. to ASTM A 6		


Ord.item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars
000001	W 16 X 10.25 X 67	40'	36,577 kg				
		12.192 mm		01249	6,096 kg		5
				10724	12,192 kg		10
				11250	18,289 kg		15

Heat nr	Heat analysis (%)																
	C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	Ti	CEV	Sn	Nb+V	
	<b>Min</b>	0,50			0,10												
	<b>Max</b>	0,23	1,60	0,035	0,045	0,40	0,60	0,45	0,35	0,150	0,050	0,150		0,45		0,150	
01249		0,08	1,05	0,026	0,027	0,16	0,008	0,43	0,16	0,11	0,005	0,023	0,040	0,001	0,33	0,03	0,028
10724		0,07	1,04	0,034	0,025	0,18	0,009	0,43	0,16	0,21	0,006	0,024	0,040	0,002	0,33	0,02	0,030
11250		0,08	1,05	0,026	0,027	0,16	0,008	0,43	0,16	0,11	0,005	0,023	0,040	0,001	0,33	0,03	0,028

Heat nr	Tensile test				
	PSI	PSI	200 mm		
	Ys	UTS	El. (%)	Y/U	
	<b>Min</b>	50.000	65.000	18,00	
	<b>Max</b>	65.000		0,85	
01249		55.245	72.210	24,28	0,77
01249		55.825	72.935	24,53	0,77
10724		55.825	73.805	25,27	0,76
10724		55.245	73.080	25,02	0,76
11250		55.825	72.935	24,53	0,77
11250		55.245	72.210	24,28	0,77

Material melted and manufactured in LUXEMBOURG

Klecker Roberto  
 Porteur de signature spéciale



ArcelorMittal Belval & Differdange