

# CERTIFIED MILL TEST REPORT



**The Best Value  
Price, Quality, Service  
All The Time.**

LOG NO. 326579 PAGE 2

BONNEY FORGE  
P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330  
(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906  
www.bonneyforge.com

**CUSTOMER:** PLESA ANAHUAC Y CIAS, S. S. DE

**Date** 10/13/09

**CUSTOMER'S Order No.:** 4948

**Bonney Order No.**

**SHIPPED TO:** SPECIALISTS IN TRANSIT  
QUIVIRA 302 DRIVE  
PANAAMERICAN IND PARK  
  
LAREDO, TX78045 MEXICO


8000040649

GRADE OR SPECIFICATION NO.  
CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.				
				SA/A105			
005	50	57631	2 3000 A105 90EL T				
			C .200 MN 1.030 P .009 S .019 SI .220				
			NI .050 CU .170 CO .005 CR .030 MO .010				
			V .000 AL .021 NB .014				
			CE(LONG FORMULA) = 0.39				
			T/S 83543 Y/S 51759 EL 29.25 RA 60.10				
			BRINELL HARDNESS1: 144 HARDNESS2: 144				
006	50	57575	2 X2 X 3/4 3000 A105 TEE T				
			C .200 MN .990 P .011 S .019 SI .240				
			NI .040 CU .130 CO .003 CR .060 MO .010				
			V .000 AL .023 NB .016				
			CE(LONG FORMULA) = 0.39				
			T/S 78125 Y/S 51000 EL 30.60 RA 63.25				
			BRINELL HARDNESS1: 139 HARDNESS2: 139				
007	50	57525	2 X2 X 1 3000 A105 TEE T				
			C .190 MN 1.010 P .011 S .020 SI .200				
			NI .030 CU .140 CO .003 CR .080 MO .020				
			V .000 AL .024 NB .016				
			CE(LONG FORMULA) = 0.39				
			T/S 80000 Y/S 49400 EL 29.00 RA 58.00				
			BRINELL HARDNESS1: 156 HARDNESS2: 153				

\*\*\*\*\* CONTINUED ON NEXT PAGE \*\*\*\*\*

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by   
Cris Boozel

**QUALITY PROCESS MANAGER**

CMTR: REV 1