



Industrial de Válvulas, S.A. de C.V.

Industria Ite 16 S/N Fracc. Industrial el Trébol de Tepozotlán, Estado de México, México C.P. 54610

CERTIFICATE OF MATERIALS & TEST REPORT (CMTR)
(CERTIFICADO DE CALIDAD DE MATERIALES Y REPORTE DE PRUEBAS CMTR)
ACCORDING TO EN 10204 TYPE 3.1

No. código interno (Product Code Nr.): **EC040ADE1MR21BY**

No. Serie (Serial Number): **16C3323**

Fecha (Date): **September 1, 2016**

No. De Tag (Tag Number):

Cientes (Customer): **PLESA ANAHUAC Y CIAS, S.A DE C.V.**

No Pedido del Cliente (Customer PO Nr.): **24165**

Partida (Customer Item): **5** Pedido Interno No (Walworth Sales Nr.): **D000060560**

Partida (Item): **5**

Linea de producto (Product line):	Cast Iron	Extremos (Ends):	FF	Operación (Operation):	Handwheel
Tipo de válvula (Type of valve):	Gate	Cuerpo (Shell):	GRAY IRON	Otros (Other requirements):	
Diámetro (Nominal diameter):	4	Interiores (Trim):	#E1 (BCE)		
Presión clase (Pressure class):	125	Figura No (Figure Nr.):	FIG W726		

COMPOSICION QUIMICA EN % (CHEMICAL COMPOSITION %)

Parte (Component)	Material (Material)	Colada (Heat)	% P	% S	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%
BONETE (BONNET)	ASTM_A_126_GR_B	C57B	0.044	0.053	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000
CUERPO (BODY)	ASTM_A_126_GR_B	C572	0.051	0.053	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000
DISCO 1 (DISC 1)	ASTM_A_126_GR_B	C57E	0.057	0.059	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000

PROPIEDADES MECANICAS (MECHANICAL TESTING)

Parte (Component)	Colada (Heat)	Condición de TT Normalizado & revenido Heat Treatment condition (Normalized & tempered)	Cedencia (Yield strength) (Kpsi)	Tensión (Tensile strength) (Kpsi)	Alar. En 2" (Elong. in 2") (% min)	Reduccion de area (Reduction of area) (% min)	Dureza (Hardness) (Bhn)		Prueba Impacto (Impact Test) (Joules)					
							1st	2nd	1st	2nd	3rd	AVG		
BONETE (BONNET)	C57B	NO APLICA NOT APPLICABLE	0.0000	41.7600	0	0	0	0	0	0	0	0	0	0
CUERPO (BODY)	C572	NO APLICA NOT APPLICABLE	0.0000	41.3250	0	0	0	0	0	0	0	0	0	0
DISCO 1 (DISC 1)	C57E	NO APLICA NOT APPLICABLE	0.0000	41.0350	0	0	0	0	0	0	0	0	0	0

TIPO DE PRUEBA (Type of test)	PRESION (Pressure) (Psi)	TIEMPO (Duration) (min)	RESULTADO (Result)	TIPO DE PRUEBA (Type of test)	RESULTADO (Result)
HIDROSTATICA DE CASCO (HYDROSTATIC SHELL)	350	0.5 min	ACEPTADO (ACCEPTED)		
PRUEBA HIDROSTATICA SELLO 1 (HIGH PRESSURE CLOSURE SIDE 1)	200	0.5 min	ACEPTADO (ACCEPTED)		
PRUEBA HIDROSTATICA SELLO 2 (HIGH PRESSURE CLOSURE SIDE 2)	200	0.5 min	ACEPTADO (ACCEPTED)		



Certificamos que este producto ha sido diseñado, fabricado y probado de acuerdo con nuestro sistema de administración de calidad y con los requisitos establecidos en una o más de las siguientes normas en su última edición. (We hereby certify this product has been designed, manufactured and tested according to our quality management system and requirements stated in one or more of the following standards on their latest edition.)

- API 599 METAL PLUG VALVES - FLANGED, THREADED AND WELDING
- API 591 PROCESS VALVE QUALIFICATION PROCEDURE
- API 623 STEEL GLOBE VALVES—FLANGED AND BUTT-WELDING ENDS, BOLTED BONNETS
- API 624 TYPE TESTING OF RISING STEM VALVES EQUIPPED WITH GRAPHITE PACKING FOR FUGITIVE EMISSIONS
- ANSI B16-10 FACE TO FACE AND END TO END DIMENSIONS OF VALVES
- ANSI B16-11 FORGED FITTINGS, SOCKET - WELDING AND THREADED
- ANSI/NACE MR0175/ISO 15156-1 MATERIALS FOR USE IN H2S-CONTAINING ENVIRONMENTS IN OIL AND GAS PRODUCTION
- NACE MR0103 MATERIAL RESISTANT TO SULFIDE STRESS CRACKING IN CORROSIVE PETROLEUM ENVIRONMENT
- MSS-5761 PRESSURE TESTING OF STEEL VALVES

Quality Assurance Department
Yolanda Ponciano Montoya