


CERTIFIED MILL TEST REPORT



LOG NO. F0000000023964

Page 1 of 1

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330

(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4906

www.bonneyforge.com

CUSTOMER: WFI INTERNATIONAL, INC.

DATE 01/17/2012

CUSTOMER

BONNEY ORDER NO. B000112572

ORDER NO.: BD00065727

PO# 12053

SHIP TO: AMERICAN DISPEATCH

REF: C1200390

302 QUIVIRA DR

IND PARK

LAREDO TX 78045

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO. CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:
23	200	58456	1 3000 A105 90EL S SA/A105
Al 0.025 C 0.210 Co 0.003 Cr 0.030 Cu 0.090 Mn 1.030 Mo 0.010 N 0.005			
Nb 0.014 Ni 0.040 P 0.008 S 0.024 Si 0.220 V 0.003			
CE(Long Formula) = 0.40			
T/S(PSI) 78,750 Y/S(PSI) 51,250 EL(%) 28.85 RA(%) 62.55			
Brinell 147 BHN 150 BHN			

1. THE MATERIAL SUPPLIED IS FREE FROM MERCURY AND RADIUM CONTAMINATION.
2. THE FITTINGS SUPPLIED ARE IN ACCORDANCE WITH PURCHASE ORDER SPECIFICATIONS.
3. THE MATERIAL SUPPLIED MEETS THE REQUIREMENTS OF NACE MRO175/ISO 15156-2.
4. CERTIFYING ASTM A105-10 / ASME SA105-10 EDITION.
5. THE FITTINGS SUPPLIED WERE NOT SUBJECTED TO ANY FORM OF WELD REPAIR.
6. THE PRODUCT SUPPLIED WAS INSPECTED IN ACCORDANCE WITH EN 10204:2004 EDITION TYPE 3.1 INSPECTION DOCUMENT. (EUROPEAN STANDARD)
7. ELONGATION TEST RESULTS ARE OBTAINED USING STANDARD ROUND SPECIMEN, 2 INCH OR 50 MM GAGE LENGTH.
8. THE MATERIAL SUPPLIED IS IN THE AS-FORGED CONDITION.

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by

Kylee Ruiz

QUALITY PROCESS MANAGER

CMTR: REV2