

**CERTIFIED MILL TEST REPORT**

**B**® The Best Value -  
Price, Quality, Service  
All The Time.

LOG NO. F0000000023963

BONNEY FORGE CORPORATION  
P.O. BOX 330 • 14486 CROGHAN PIKE • MOUNT UNION, PA 17086-0330  
(814) 542-2545 • (800) 345-7546 • FAX (814) 542-4908  
www.bonneyforge.com

CUSTOMER: WFI INTERNATIONAL, INC.

DATE 01/17/2012

CUSTOMER  
ORDER NO.: BD00065727

BONNEY ORDER NO. B000112572


SHIP TO: AMERICAN DISPEATCH  
302 QUIVIRA DR  
IND PARK  
LAREDO TX 78045

PO# 12053  
REF: C1200390

ITEM	QUANTITY	LOT NO.	GRADE OR SPECIFICATION NO.	CHEMICAL ANALYSIS, PHYSICAL PROPERTIES, REMARKS:
18	50	58509	2 3000 HOT-DIP 90EL T	SA/A105 Al 0.020 C 0.200 Co 0.002 Cr 0.040 Cu 0.060 Mn 1.070 Mo 0.000 Nb 0.015 Ni 0.020 P 0.006 S 0.023 Si 0.220 V 0.004 T/S(PSI) 78,750 Y/S(PSI) 48,750 EL(%) 30.00 RA(%) 62.05 Brinell 144 BHN 141 BHN
20	50	58421	3/4 3000 A105 TEE S	SA/A105 C 0.190 Cb 0.000 Co 0.004 Cr 0.080 Cu 0.130 Mn 1.030 Mo 0.010 Ni 0.040 P 0.008 S 0.020 Si 0.170 V 0.004 CE(Long Formula) = 0.39 T/S(PSI) 76,875 Y/S(PSI) 51,250 EL(%) 33.20 RA(%) 66.10 Brinell 139 BHN 139 BHN
21	50	58394	2 3000 A105 45EL S	SA/A105 C 0.200 Cb 0.000 Co 0.002 Cr 0.030 Cu 0.100 Mn 0.990 Mo 0.010 Ni 0.030 P 0.007 S 0.019 Si 0.170 V 0.004 CE(Long Formula) = 0.38 T/S(PSI) 75,000 Y/S(PSI) 51,875 EL(%) 30.30 RA(%) 62.30 Brinell 135 BHN 135 BHN
22	50	58491	1 3000 A105 45EL S	SA/A105 Al 0.028 C 0.200 Co 0.002 Cr 0.040 Cu 0.070 Mn 1.020 Mo 0.000 N 0.003 Nb 0.015 Ni 0.020 P 0.008 S 0.022 Si 0.190 V 0.004 CE(Long Formula) = 0.38 T/S(PSI) 75,625 Y/S(PSI) 47,500 EL(%) 30.35 RA(%) 62.55 Brinell 144 BHN 141 BHN

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

by



Kylee Ruiz  
QUALITY PROCESS MANAGER

CMTR: REV2