CERTIFIED MILL TEST REPORT



LOG NO.

F00000000062417

Page 1 of 1

BONNEY FORGE CORPORATION

P.O. BOX 330 • 14496 CROGHAN PIKE • MOUNT UNION, PA 17066-0330 (B14) 542-2545 • (800) 345-7546 • FAX (B14) 542-4906

www.bonneyforge.com

CUSTOMER: WFI INTERNATIONAL, INC.

DATE 08/27/2014

CUSTOMER

BONNEY ORDER NO.

ORDER NO.:

SHIP TO: WFI INTERNATIONAL, INC.

P. O. BOX 7303 HOUSTON TX 77248 United States

)ii:	M QU	ANTITY LOT NO.			ADE OR SPECIFICATION N YSIS, PHYSICAL PROPER		
1	1	59313	2 X2 X 1 3000 A105 TEE	S	SA/A	A105	
			Al 0.024 C 0.210	Co 0.005 Cr 0.050	Cu 0.070 Mn 0.980	Mo 0.006 N 0.003	
				P 0.005 S 0.018			
			CE(Long Form				
			T/S(PSI) 79,422	Y/S(PSI) 52,178	EL(%) 33.50	RA(%) 61.47	
			Brinell	141 BHN	141 BHN		

- 1. THE FITTINGS SUPPLIED ARE IN ACCORDANCE WITH PURCHASE ORDER SPECIFICATIONS.
- 2. THE MATERIAL SUPPLIED MEETS THE REQUIREMENTS OF NACE MR0175/ISO 15156-2.
- 3. CERTIFYING ASTM A105-13 / ASME SA105-10 EDITION.
- 4. THE PRODUCT SUPPLIED WAS INSPECTED IN ACCORDANCE WITH EN 10204:2004 EDITION TYPE 3.1 INSPECTION DOCUMENT. (EUROPEAN STANDARD)
- ELONGATION TEST RESULTS ARE OBTAINED USING STANDARD ROUND SPECIMEN, 2 INCH OR 50 MM GAGE LENGTH.

We certify that the data on this sheet is a true copy taken from our records of material furnished us by the production mill, or as obtained by additional laboratory checks.

CMTR: REV2

by

Kylee Ruiz

QUALITY PROCESS MANAGER