## **Material Test Report**

COFFER\* an AFG Da Company

Heat Code: YRR

Coffer Corp.

An AFGlobal Company

13770 Industrial Rd. Houston, TX 77015

ISO 9001:2008 Certified

Sales: (713) 868-4421 Fax: (713) 455-8366

PLESA STEEL INC. 00012015 PO: 261 Sales Order: 138418 Line: 19 11811 NORTH FRWY STE 500 Item Code: 0601300101-0021F Qty Shipped: 20 Item Desc: FLG 03.00 0600 WN RF STD A105 Houston, TX 77060 NRM COFFR Supplier: CMC-TEXAS Supplier Heat: 3048919

Spec: ASTM A105/A105N-(13)/ASME SA 105/SA 105N-(13) Section II Part A - Normalized

Eler	nent (%wt)	Ladle	Product	EPCRA	CAS#	Element (%wt)	Ladle	Product	EPCRA	CAS#
C	Carbon	0.19				Cr Chromium	0.09		<b>√</b>	7440-47-3
Mn	Manganese	0.95		<b>√</b>	7439-96-5	Mo Molybdenum	0.038			
P	Phosphorous	0.012				V Vanadium	0.001			
S	Sulphur	0.014				Cb Columbium	0.002			
Si	Silicen	0.26				C.E.	0.40			
Cu	Copper	0.27		1	7440-50-8	CuNiCrMoV	0.489			
Ni	Nickel	0.09		V	7440-02-0	CrMo	0.13			

Yield (ksi) 47.3 EF Y	Testing	:	Heat Treat
RA (%) 54 Norm. Cooling Type AIR  Tensile Specimen Size (in) .492  Tensile (ksi) 79.4 Other  Yield (ksi) 47.3 EF Y	152 - 152	Norm. Temp. (F)	1650
Tensile Specimen Size (in) .492  Tensile (ksi) 79.4  Yield (ksi) 47.3  EF Y	3.0	Norm. (Hrs)	4
Tensile (ksi)         79.4         Other           Yield (ksi)         47.3         EF         Y	54	Norm. Cooling Type	AIR
Yield (ksi) 47.3 EF Y	.492		
	79.4		Other
Gauge Length 2 Fully Killed Y	47.3	EF	Y
	2	Fully Killed	Y
		1	
		30 54 .492 79.4	152 - 152 Norm. Temp. (F) 30 Norm. (Hrs) 54 Norm. Cooling Type 492 79.4 47.3 EF

Product compliant with NACE MR0175 / ISO 15156 and NACE MR0103 latest edition and flange dimensions to ASME B16.5 - 2013.

- \* No Weld repair performed.
- \* Ladle Chemical Analysis results are reported from the raw material suppliers MTR.
- \* Forgings are capable of passing hydrostatic test compatible with the appropriate rating.
- \* Elongation taken from a round specimen.
- \* Yield strength was determined using the .2% offset method.
- \* All material supplied under this order is certified to be free of mercury contamination and no mercury bearing equipment was used in manufacturing, fabrication or testing.
- \* When reported on MTR: Tensile Testing Per ASTM E8; Brinell Hardness Per ASTM E10; Charpy Testing
- \* AF Global manufactures materials according to a certified Quality Management System conforming to ISO 9001:2008 and PED 97/23/EC, Annex 1, Section 4.3

The recording of false, fictitious, or fraudulent statement or entries on this document may be punishable as a felony under federal statute.

EPCRA Supplier Notification: This product may contain one or more toxic chemicals subject to the reporting requirements of Section 313 of the Emergency Planning and Community Right-to-Know Act (Title III of the Superfund Amendments and Reauthorization Act of 1985) and 40 C.F.R. Part 372. Potentially reportable chemicals are indicated with a checkmark in the "EPCRA" column and a Chemical Abstract Services (CAS) registry number is provided for each such chemical in addition to the percent by weight of the chemical present in this product. It is your responsibility alone to determine whether your facility is required to submit a Toxic Release Inventory Report under EPCRA Section 313.

Certification No.:

1131932

Certification Date: 9/3/2014

Juan Diaz

This report is issued in compliance with the requirements of EN10204 3.1 / ISO 10474 3.1 b

Rina Sane - Metallurgical Lab Manager