## **Material Test Report**

Heat Code: ZAX

An Ameri-Forge Group Company 13770 Industrial Rd, Houston, TX 77015

Line: 4

ISO 9001:2000 Certified

Sales: (713) 868-4421 Fax: (713) 455-8366

SA DE CV AV. VALLE DE LAS

Item Code: 0151400101-0020F

Qtv Shipped: 100

NHT COFFR

54940 TULTITLAN, EDO MEX

Item Desc: FLG 04.00 0150 WN RF STD A105 Supplier: CMC

Sales Order: 61702

Supplier Heat: 258976

Spec ASTM A 105/A 105M-03/ASME SA 105/SA 105M-04, Melt Practice EF

PO: 35573644

| Element (%wt) | Ladle | Product EPC | RA CAS#   | Element   | (%wt) | Ladle | Product | EPCRA CAS#  |
|---------------|-------|-------------|-----------|-----------|-------|-------|---------|-------------|
| C Carbon      | 0 19  |             |           | Cr Chromi | um    | 0.09  |         | √ 7440-47-3 |
| Mn Manganese  | 0 89  | ✓           | 7439-96-5 | Mo Molybo | ienum | 0.030 |         |             |
| P Phosphorous | 0.010 |             |           | V Vanadi  | .um   | 0.001 |         |             |
| S Sulphur     | 0.021 |             |           | Cb Columb | ium   | 0.001 |         |             |
| Si . Silicon  | 0.18  |             |           | C.E.      |       | 0.389 |         |             |
| Cu Copper     | 0.29  | √.          | 7440-50-8 | CuNiCrMo  |       | 0.52  |         |             |
| Ni Nickel     | 0 11  | 7           | 7440-02-0 | CrMo      |       | 0 12  |         |             |
|               |       |             |           |           |       |       |         |             |
|               |       |             |           |           |       |       |         |             |

| Mechanica                  |                   | -       |           | Other |          |
|----------------------------|-------------------|---------|-----------|-------|----------|
| Test Lab                   | AFG               | Country | of Origin |       | USA (US) |
| Test Bar Size              | SACRIFICIAL PIECE | EF      |           |       | Y        |
| HBW                        | 163-163           |         |           |       |          |
| Elg (%)                    | 30.0              |         |           |       |          |
| PA (%)                     | 47.0              |         |           |       |          |
| Tensile Specimen Size (in) | 0 501             |         |           |       |          |
| Tensile (ksi)              | 78.5              |         |           |       |          |
| Yield (ksi)                | 46 8              |         |           |       |          |
| Gauge Length               | 2 00              |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |
|                            |                   |         |           |       |          |

Product compliant with NACE MRO175, latest edition

Product compliant with and meets all requirements of ASTM A105/ASME SA105-05 No Weld repair performed Chemical Analysis results shown are actual. Forgings are capable of passing hydrostatic test compatible with the appropriate rating Elongation taken from a round specimen. All material supplied under this order is certified to be free of mercury contamination and no mercury bearing equipment was used in manufacturing, fabrication or testing. Yield strength was determined using the 0.2% offset method

EPCRA Supplier Notification: This product may contain one or more toxic chemicals subject to the reporting requirements of Section 313 of the Emergency Planning and Community Right-to-Know Act (Title III of the Superfund Amendments and Reauthorization Act of 1986) and 40 C F R. Part 372. Potentially reportable chemicals are indicated with a checkmark in the "EPCRA" column and a Chemical Abstract Services (CAS) registry number is provided for each such chemical in addition to the percent by weight of the chemical present in this product. It is your responsibility alone to determine whether your facility is required to submit a Toxic Release Inventory Report under EPCRA Section 313.

Certification No:

127774

Certification Date:

This report is issued in compliance with the requirements of EN10204 3 1 / ISO 10474 3 1 b

Kevin Papich - Tech. Svcs. Manager

