

Material Test Report

Heat Code: GGC

An Ameri-Forge Group Company 13770 Industrial Rd., Houston, TX 77015

ISO 9001:2000 Certified

Sales: (713) 868-4421 Fax: (713) 455-8366

PLESA ANAHUAC Y CIAS

SA DE CV AV. VALLE DE LAS ALAMEDAS 66-0

54940 TULTITLAN, EDO MEX

PO: 5526

Sales Order: 67635

Line: 8

Item Code: 0152400100-0020F

Qty Shipped: 180

Item Desc: FLG 04.00 0150 SO RF

A105 NHT COFFR

Supplier Heat: 3006180

Supplier: CMC Spec: ASTM A 105/A 105M-(05)/ASME SA 105/SA 105M-(08a) Section II Part A

C Carbon 0.19 Cr Chromium 0.08 ✓ 7440-4 Mn Manganese 0.89 ✓ 7439-96-5 Mo Molybdenum 0.016 P Phosphorous 0.010 V Vanadium 0.003 S Sulphur 0.013 Cb Columbium 0.001 Si Silicon 0.18 C.E. 0.375 Cu Copper 0.20 ✓ 7440-50-8 CuNiCrMo 0.36 Ni Nickel 0.06 ✓ 7440-02-0 CrMo 0.10	Elen	ent (%wt)	Ladle	Product	EPCR	A CAS#	Elen	nent	(%wt)	Ladle	Product	EPCRA	CAS#
P Phosphorous 0.010 V Vanadium 0.003 S Sulphur 0.013 Cb Columbium 0.001 Si Silicon 0.18 C.E. 0.375 Cu Copper 0.20 ✓ 7440-50-8 CuNiCrMo 0.36	С	Carbon	0.19				Cr	Chrom	ium	0.08		√ -	7440-47-3
S Sulphur 0.013 Cb Columbium 0.001 Si Silicon 0.18 C.E. 0.375 Cu Copper 0.20 ✓ 7440-50-8 CuNiCrMo 0.36	Mn	Manganese	0.89		✓	7439-96-5	Мо	Mo1yb	denum	0.016			
Si Silicon 0.18 C.E. 0.375 Cu Copper 0.20 ✓ 7440-50-8 CuNiCrMo 0.36	P	Phosphorous	0.010				v	Vanad	ium	0.003			
Cu Copper 0.20 ✓ 7440-50-8 CuNiCrMo 0.36	S	Sulphur	0.013				Cb	Colum	bium	0.001			
	Si	Silicon	0.18				C.E			0.375			
Ni Nickel 0.06 √ 7440-02-0 CrMo 0.10	Cu	Copper	0.20		✓	7440-50-8	CuN	iCrMo		0.36			
	Ni	Nickel	0.06		✓	7440-02-0	CrM	5		0.10			
							•						

Mechanic	al .		Other	
Test Lab	AFG	EF	Y	
Test Bar Size	SACRIFICIAL PIECE	•		
нв₩	149-149	•		
Elg (%)	31.0			
RA (%)	65.0	•		
Tensile Specimen Size (in)	0.245			
Tensile (ksi)	77.0	:		
Yield (ksi)	45.3	•		
Gauge Length	1.00			
		•		
		:		

Product compliant with NACE MR0175 / ISO 15156, latest edition and dimensions to ANSI B16.5 Product compliant with and meets all requirements of ASTM A105/ASME SA105, latest edition.

No Weld repair performed. Chemical Analysis results shown are actual. Forgings are capable of passing hydrostatic test compatible with the appropriate rating. Elongation taken from a round specimen. All material supplied under this order is certified to be free of mercury contamination and no mercury bearing equipment was used in manufacturing, fabrication or testing. Yield strength was determined using the 0.2% offset method.

EPCRA Supplier Notification: This product may contain one or more toxic chemicals subject to the reporting requirements of Section 313 of the Emergency Planning and Community Right-to-Know Act (Title III of the Superfund Amendments and Reauthorization Act of 1986) and 40 C.F.R. Part 372. Potentially reportable chemicals are indicated with a checkmark in the "EPCRA" column and a Chemical Abstract Services (CAS) registry number is provided for each such chemical in addition to the percent by weight of the chemical present in this product. It is your responsibility alone to determine whether your facility is required to submit a Toxic Release Inventory Report under EPCRA Section 313.

Certification No.:

155509

Certification Date:

12/10/2008

Nicholas Tepovich - Metallurgic Lab Manager

Vielelas Tepare

This report is issued in compliance with the requirements of EN10204 3.1 / ISO 10474 3.1.b