

Material Test Report

Heat Code: GMA

An Ameri-Forge Group Company 13770 Industrial Rd. Houston, TX 77015

ISO 9001:2000 Certified

Sales: (713) 868-4421 Fax: (713) 455-8366

PLESA ANAHUAC Y CIAS SA DE CV AV. VALLE DE LAS ALAMEDAS 66-0

PO: 5647 Item Code: 0151400102-0020F

Line: 10 Sales Order: 68015 Qty Shipped: 25

Supplier Heat: 3006379

Item Desc: FLG 04.00 0150 WN RF XH

Supplier: CMC 54940 TULTITLAN, EDO, MEX Spec: ASTM A 105/A 105M-(05)/ASME SA 105/SA 105M-(08a) Section II Part A

C Carbon 0.19	Elen	ient	(%wt)	Ladle	Product	EPCR#	CAS#	Eler	nent	(%wt)	Ladle	Product	EPCRA	CAS#
P Phosphorous 0.009 V Vanadium 0.002 S sulphur 0.015 Cb Columbium 0.003 Si Silicon 0.18 C.E. 0.38113 Cu Copper 0.26 ✓ 7440-50-8 CunicrMo 0.46	C	Carbon		0.19				: Cr	Chrom	ium	0.08		√ 7.	440-47-3
P Phosphorous 0.009 V Vanadium 0.002 S Sulphur 0.015 Cb Columbium 0.003 Si Silicon 0.18 C.E. 0.38113 Cu Copper 0.26 ✓ 7440-50-8 CuNiCrMo 0.46	Mn	Mangan	iese	0.87		1	7439-96-5	Mo	Molyb	denum	0.03			
Si Silicon 0.18 C.E. 0.38113 Cu Copper 0.26 ✓ 7440-50-8 CUNICIMO 0.46								· v	Vanad	ium	0.002			
Cu Copper 0.26 ✓ 7440-50-8 CUNICIMO 0.46	S	Sulpho	ir	0.015				: cb	Colum	bium				
Cu Copper 0.26 ✓ 7440-50-8 CUNICTMO 0.46	Si	Silico	on.	0.18				C.E	.*.:		0.38113			
The second secon				0.26		1	7440-50-8	Cun	iCrMo		0.46			
						/	7440-02-0	CrM	o		0.11			

Mechanical Te	esting	•	Other
Test Lab	AFG	MILL	CMC
Test Bar Size	SACRIFICIAL PIECE	мнс	3006379
HBW	149 - 149		
Elg (%)	35		
RA (%)	62		
Tensile Specimen Size (in)	. 247	•	
Tensile (ksi)	77.8	•	
Yield (ksi)	479	•	
Gauge Length	1		
		•	
		•	

Product compliant with NACE MR0175 / ISO 15156, latest edition and dimensions to ANSI B16.5 Product compliant with and meets all requirements of ASTM A105/ASME SA105, latest edition. No Weld repair performed. Chemical Analysis results shown are actual. Forgings are capable of passing hydrostatic test compatible with the appropriate rating. Elongation taken from a round specimen. All material supplied under this order is certified to be free of mercury contamination and no mercury bearing equipment was used in manufacturing, fabrication or testing. Yield strength was determined using the 0.2% offset method.

EPCRA Supplier Notification: This product may contain one or more toxic chemicals subject to the reporting requirements of Section 313 of the Emergency Planning and Community Right-to-Know Act (Title III of the Superfund Amendments and Reauthorization Act of 1986) and 40 C.F.R. Part 372. Potentially reportable chemicals are indicated with a checkmark in the "EPCRA" column and a Chemical Abstract Services (CAS) registry number is provided for each such chemical in addition to the percent by weight of the chemical present in this product. It is your responsibility alone to determine whether your facility is required to submit a Toxic Release Inventory Report under EPCRA Section 313.

Certification No.:

160427

Certification Date:

1/16/2009

Nicholas Tepovich - Metallurgic Lab Manager

Analalas Lapare

This report is issued in compliance with the requirements of EN10204 3.1 / ISO 10474 3.1.b