

Material Test Report

Heat Code: GGM

An Ameri-Forge Group Company 13770 Industrial Rd., Houston, TX 77015

ISO 9001:2000 Certified

Sales: (713) 868-4421 Fax: (713) 455-8366

PLESA ANAHUAC Y CIAS SA DE CV AV. VALLE DE LAS

Item Code: 0601600402-0021F

Sales Order: 67635 Line: 21 Qty Shipped: 30

ALAMEDAS 66-0

PO: 5526

A105

Item Desc: FLG 06.00 0600 WN RJ XH

NRM COFFR

54940 TULTITLAN, EDO MEX

Supplier Heat: 3006161 Supplier: CMC

Spec: ASTM A 105/A 105M-(05)/ASME SA 105/SA 105M-(08a) Section II Part A -

C Carbon 0.20 Ni Nickel 0.07 Mn Manganese 0.89 ✓ 7439-96-5 Cr Chromium 0.13 P Phosphorous 0.019 Mo Molybdenum 0.021 S Sulphur 0.019 V Vanadium 0.002 Si Silicon 0.210 Cb Columbium 0.001	0.89	Elem	ent (%w	rt) Ladle	Product	EPCRA CAS#	Element (%wt)	Ladle	Product EPCRA CAS#
P Phosphorous 0.019 Mo Molybdenum 0.021 S Sulphur 0.019 V Vanadium 0.002	0.019 Mo Molybdenum 0.021 0.019 V Vanadium 0.002 0.210 Cb Columbium 0.001	С	Carbon	0.20			Ni Nickel	0.07	✓ 7440-02-0
S Sulphur 0.019 V Vanadium 0.002	0.019 V Vanadium 0.002 0.210 Cb Columbium 0.001	Mn	Manganese	0.89		√ 7439-96-5	Cr Chromium	0.13	√ 7440-47-3
:	0.210 Cb Columbium 0.001	P	Phosphorous	0.019			Mo Molybdenum	0.021	
Si Silicon 0.210 Cb Columbium 0.001		S	Sulphur	0.019			V Vanadium	0.002	
	0.24 ✓ 7440-50-8 C.E. 0.40	Si	Silicon	0.210			Cb Columbium	0.001	
Cu copper 0.24 ✓ 7440-50-8 C.E. 0.40	:	Cu	Copper	0.24		√ 7440-50-8	C.E.	0.40	
							:		

Mecha	nical	F	leat Treat	
Test Lab	AFG	Norm. Temp. (F)	1675	
Test Bar Size	SACRIFICIAL PIECE	Norm. (Hrs)	4.0	
HBW	156-156	Norm, Cooling Type	AIR	
Elg (%)	34.0	Norm. Location	AFG	
RA (%)	60.0			
Tensile Specimen Size (in)	0.497			
Tensile (ksi)	75.6			
Yield (ksi)	45.1			
Gauge Length	2.00			
		:		

Product compliant with NACE MR0175, latest edition and dimensions to ANSI B16.5 No Weld repair performed. Chemical Analysis results shown are actual. Forgings are capable of passing hydrostatic test compatible with the appropriate rating. Elongation taken from a round specimen. All material supplied under this order is certified to be free of mercury contamination and no mercury bearing equipment was used in manufacturing, fabrication or testing. Yield strength was determined using the 0.2% offset method.

EPCRA Supplier Notification: This product may contain one or more toxic chemicals subject to the reporting requirements of Section 313 of the Emergency Planning and Community Right-to-Know Act (Title III of the Superfund Amendments and Reauthorization Act of 1986) and 40 C.F.R. Part 372. Potentially reportable chemicals are indicated with a checkmark in the "EPCRA" column and a Chemical Abstract Services (CAS) registry number is provided for each such chemical in addition to the percent by weight of the chemical present in this product. It is your responsibility alone to determine whether your facility is required to submit a Toxic Release Inventory Report under EPCRA Section 313.

Certification No.:

156073

Certification Date:

12/17/2008

Nicholas Tepovich - Metallurgic Lab Manager