

Certificate/Serial/Job No: YJ135

Quality Department: John Ho

Quantity	Size (NPS)	Class	Product	Description	Type	SONumber	Line	Sold to	Date
33	4	300	/ 103060	DSI 23XUF	GATE				9/22/2012

<b>Pressure Test:</b> API598	<input checked="" type="checkbox"/> Satisfactory	<b>Shell Pressure :</b> 1125 psi 7756.6 kPa	<b>BackSeat :</b> 825 psi 5688.2 kPa	<b>Seat Pressure</b> 825 psi 5688.17 kPa	<b>Seat Air Pressure</b> 80 psi 551.58 kPa
------------------------------	--	--	---	---	---

Part	Specif.	HEAT#	Chemical Composition [%]													Mechanical Properties								
			C	Si	Mn	P	S	Ni	Cr	Mo	Cu	V	W	Nb	Al	N	Ceq	Tensile [ksi] [MPa]	Yield [ksi] [MPa]	Elong [%]	Reduc [%]	Hard [HB]	Ch.1 [J]	Ch.2 [J]

YJ135 / 1

BODY	ASTM A216 WCB-2008	A 12934	0.210	0.41	0.88	0.026	0.015	0.031	0.058	0.003	0.026	0.004		0.056	0.37	72.50	43.21	32	57	149								N
BONNET	ASTM A216 WCB-2008	A 12417	0.200	0.45	0.95	0.020	0.008	0.029	0.070	0.002	0.036	0.009		0.05	0.38	74.68	44.37	32	57	152								N
WEDGE	ASTM A217 CA15-2007	D 9100	0.11	0.89	0.77	0.028	0.010	0.131	12.80	0.095	0.036					104.26	73.66	20	49	270							N	

YJ135 / 2

BODY	ASTM A216 WCB-2008	A 12782	0.210	0.48	0.98	0.028	0.016	0.072	0.098	0.014	0.038	0.005		0.049	0.40	74.97	44.81	30	56	152								N
BONNET	ASTM A216 WCB-2008	A 12419	0.220	0.43	0.90	0.031	0.014	0.024	0.064	0.004	0.029	0.005		0.017	0.39	73.95	43.50	32	57	150								N
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013					102.81	73.23	19	49	268							N	

YJ135 / 3

BODY	ASTM A216 WCB-2008	A 12932	0.200	0.40	0.87	0.026	0.011	0.024	0.065	0.001	0.034	0.009		0.01	0.36	76.42	45.53	26	53	154								N
BONNET	ASTM A216 WCB-2008	A 12422	0.200	0.42	0.87	0.024	0.010	0.028	0.062	0.004	0.033	0.010		0.018	0.36	74.53	44.37	32	56	152								N
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013					102.81	73.23	19	49	268							N	

YJ135 / 4

BODY	ASTM A216 WCB-2008	A 12930	0.220	0.41	0.91	0.025	0.011	0.021	0.049	0.006	0.032	0.005		0.011	0.39	76.42	45.82	26	54	155								N
BONNET	ASTM A216 WCB-2008	A 12784	0.210	0.43	0.84	0.026	0.012	0.031	0.064	0.002	0.037	0.005		0.012	0.37	74.68	44.52	31	56	153								N
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013					102.81	73.23	19	49	268							N	

YJ135 / 5

BODY	ASTM A216 WCB-2008	A 12933	0.200	0.45	0.99	0.025	0.010	0.025	0.059	0.001	0.038	0.005	0.058	0.38	74.82	44.37	30	56	152	N
															515.87	305.9				
BONNET	ASTM A216 WCB-2008	A 12780	0.200	0.40	0.91	0.025	0.012	0.053	0.098	0.010	0.036	0.004	0.005	0.38	76.56	45.53	26	54	158	N
															527.86	313.9				
WEDGE	ASTM A217 CA15-2007	D 9100	0.11	0.89	0.77	0.028	0.010	0.131	12.80	0.095	0.036				104.26	73.66	20	49	270	N
															718.85	507.9				

**YJ135 / 6**

BODY	ASTM A216 WCB-2008	A 12935	0.220	0.42	0.88	0.026	0.014	0.029	0.080	0.005	0.077	0.005	0.006	0.39	74.53	44.37	32	57	152	N
															513.87	305.9				
BONNET	ASTM A216 WCB-2008	A 12650	0.210	0.45	0.92	0.028	0.013	0.043	0.097	0.006	0.038	0.007	0.038	0.39	72.50	43.07	32	58	148	N
															499.87	297				
WEDGE	ASTM A217 CA15-2007	D 9101	0.10	0.99	0.71	0.026	0.011	0.156	12.90	0.099	0.038				106.14	75.55	20	53	265	N
															731.81	520.9				

**YJ135 / 7**

BODY	ASTM A216 WCB-2008	A 13215	0.220	0.45	0.90	0.026	0.012	0.020	0.056	0.001	0.040	0.005	0.031	0.39	76.42	45.82	26	53	156	N
															526.9	315.9				
BONNET	ASTM A216 WCB-2008	A 12771	0.200	0.44	0.91	0.028	0.018	0.028	0.056	0.005	0.031	0.003	0.045	0.37	76.56	45.97	26	52	158	N
															527.86	317				
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268	N
															708.85	504.9				

**YJ135 / 8**

BODY	ASTM A216 WCB-2008	A 13217	0.200	0.43	0.88	0.023	0.010	0.049	0.089	0.007	0.039	0.006	0.013	0.37	73.95	43.79	32	57	150	N
															509.87	301.9				
BONNET	ASTM A216 WCB-2008	A 12769	0.200	0.45	0.88	0.028	0.016	0.069	0.098	0.077	0.038	0.007	0.009	0.39	76.42	45.53	26	54	156	N
															526.9	313.9				
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268	N
															708.85	504.9				

**YJ135 / 9**

BODY	ASTM A216 WCB-2008	A 12785	0.200	0.46	0.90	0.026	0.015	0.025	0.066	0.002	0.029	0.005	0.041	0.37	75.40	44.95	27	56	152	N
															519.86	309.9				
BONNET	ASTM A216 WCB-2008	A 12776	0.210	0.46	0.83	0.022	0.009	0.030	0.050	0.001	0.037	0.004	0.02	0.36	76.42	45.82	26	54	155	N
															526.9	315.9				
WEDGE	ASTM A217 CA15-2007	D 9100	0.11	0.89	0.77	0.028	0.010	0.131	12.80	0.095	0.036				104.26	73.66	20	49	270	N
															718.85	507.9				

**YJ135 / 10**

BODY	ASTM A216 WCB-2008	A 12935	0.220	0.42	0.88	0.026	0.014	0.029	0.080	0.005	0.077	0.005	0.006	0.39	74.53	44.37	32	57	152	N
															513.87	305.9				
BONNET	ASTM A216 WCB-2008	A 12773	0.210	0.42	0.90	0.035	0.019	0.042	0.062	0.001	0.030	0.004	0.011	0.38	73.37	43.36	32	57	150	N
															505.87	299				
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268	N
															708.85	504.9				

**YJ135 / 11**

BODY	ASTM A216 WCB-2008	A 13217	0.200	0.43	0.88	0.023	0.010	0.049	0.089	0.007	0.039	0.006	0.013	0.37	73.95	43.79	32	57	150	N
															509.87	301.9				
BONNET	ASTM A216 WCB-2008	A 12789	0.210	0.41	0.91	0.028	0.017	0.031	0.051	0.005	0.051	0.003	0.033	0.38	74.53	44.23	32	57	152	N
															513.87	305				
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268	N
															708.85	504.9				

**YJ135 / 12**

BODY	ASTM A216 WCB-2008	A 12939	0.210	0.40	0.89	0.023	0.010	0.021	0.053	0.003	0.039	0.004	0.023	0.37	73.95	43.79	32	57	151	N
															509.87	301.9				
BONNET	ASTM A216 WCB-2008	A 12770	0.210	0.45	0.93	0.033	0.016	0.032	0.088	0.008	0.029	0.004	0.013	0.39	74.68	44.37	31	56	151	N
															514.90	305.9				

WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013			102.81	73.23	19	49	268		N
														708.85	504.9					

**YJ135 / 13**

BODY	ASTM A216 WCB-2008	A 12425	0.220	0.48	0.90	0.026	0.014	0.040	0.093	0.003	0.034	0.008	0.059	0.40	75.98	45.82	26	55	154		N
															523.86	315.9					
BONNET	ASTM A216 WCB-2008	A 12419	0.220	0.43	0.90	0.031	0.014	0.024	0.064	0.004	0.029	0.005	0.017	0.39	73.95	43.50	32	57	150		N
															509.87	299.9					
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268		N
															708.85	504.9					

**YJ135 / 14**

BODY	ASTM A216 WCB-2008	V 14477	0.206	0.480	0.789	0.019	0.012	0.055	0.032	0.012	0.034	0.003	0.048	0.36	71.78	43.50	33	60	137		N
															494.91	299.9					
BONNET	ASTM A216 WCB-2008	A 12782	0.210	0.48	0.98	0.028	0.016	0.072	0.098	0.014	0.038	0.005	0.049	0.40	74.97	44.81	30	56	152		N
															516.9	309					
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268		N
															708.85	504.9					

**YJ135 / 15**

BODY	ASTM A216 WCB-2008	A 12934	0.210	0.41	0.88	0.026	0.015	0.031	0.058	0.003	0.026	0.004	0.056	0.37	72.50	43.21	32	57	149		N
															499.87	297.9					
BONNET	ASTM A216 WCB-2008	A 12786	0.200	0.42	0.89	0.023	0.013	0.034	0.059	0.002	0.033	0.005	0.01	0.37	73.37	43.50	32	57	150		N
															505.87	299.9					
WEDGE	ASTM A217 CA15-2007	D 9101	0.10	0.99	0.71	0.026	0.011	0.156	12.90	0.099	0.038				106.14	75.55	20	53	265		N
															731.81	520.9					

**YJ135 / 16**

BODY	ASTM A216 WCB-2008	A 12934	0.210	0.41	0.88	0.026	0.015	0.031	0.058	0.003	0.026	0.004	0.056	0.37	72.50	43.21	32	57	149		N
															499.87	297.9					
BONNET	ASTM A216 WCB-2008	A 12650	0.210	0.45	0.92	0.028	0.013	0.043	0.097	0.006	0.038	0.007	0.038	0.39	72.50	43.07	32	58	148		N
															499.87	297					
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268		N
															708.85	504.9					

**YJ135 / 17**

BODY	ASTM A216 WCB-2008	A 12785	0.200	0.46	0.90	0.026	0.015	0.025	0.066	0.002	0.029	0.005	0.041	0.37	75.40	44.95	27	56	152		N
															519.86	309.9					
BONNET	ASTM A216 WCB-2008	A 12653	0.200	0.45	0.88	0.026	0.013	0.030	0.069	0.004	0.036	0.006	0.012	0.37	74.24	44.37	30	57	151		N
															511.87	305.9					
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268		N
															708.85	504.9					

**YJ135 / 18**

BODY	ASTM A216 WCB-2008	A 13218	0.200	0.45	0.97	0.024	0.012	0.051	0.078	0.005	0.036	0.009	0.014	0.39	76.42	45.39	26	53	155		N
															526.9	313					
BONNET	ASTM A216 WCB-2008	A 12787	0.210	0.42	0.90	0.030	0.014	0.030	0.061	0.004	0.037	0.005	0.014	0.38	72.79	43.21	33	58	149		N
															501.87	297.9					
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268		N
															708.85	504.9					

**YJ135 / 19**

BODY	ASTM A216 WCB-2008	A 12936	0.220	0.42	0.94	0.025	0.012	0.030	0.082	0.012	0.077	0.005	0.019	0.40	75.40	44.95	26	53	155		N
															519.86	309.9					
BONNET	ASTM A216 WCB-2008	A 12773	0.210	0.42	0.90	0.035	0.019	0.042	0.062	0.001	0.030	0.004	0.011	0.38	73.37	43.36	32	57	150		N
															505.87	299					
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268		N
															708.85	504.9					

**YJ135 / 20**

BODY	ASTM A216 WCB-2008	A 12933	0.200	0.45	0.99	0.025	0.010	0.025	0.059	0.001	0.038	0.005	0.058	0.38	74.82	44.37	30	56	152		N
															515.87	305.9					
BONNET	ASTM A216 WCB-2008	A 12647	0.220	0.47	0.89	0.032	0.018	0.033	0.074	0.005	0.064	0.006	0.027	0.39	73.37	43.07	33	57	149		N
															505.87	297					
WEDGE	ASTM A217 CA15-2007	D 9100	0.11	0.89	0.77	0.028	0.010	0.131	12.80	0.095	0.036				104.26	73.66	20	49	270		N
															718.85	507.9					

**YJ135 / 21**

BODY	ASTM A216 WCB-2008	A 12653	0.200	0.45	0.88	0.026	0.013	0.030	0.069	0.004	0.036	0.006	0.012	0.37	74.24	44.37	30	57	151		N
															511.87	305.9					
BONNET	ASTM A216 WCB-2008	A 12784	0.210	0.43	0.84	0.026	0.012	0.031	0.064	0.002	0.037	0.005	0.012	0.37	74.68	44.52	31	56	153		N
															514.90	307					
WEDGE	ASTM A217 CA15-2007	D 9101	0.10	0.99	0.71	0.026	0.011	0.156	12.90	0.099	0.038				106.14	75.55	20	53	265		N
															731.81	520.9					

**YJ135 / 22**

BODY	ASTM A216 WCB-2008	A 12931	0.220	0.42	0.89	0.026	0.013	0.022	0.098	0.015	0.036	0.006	0.021	0.40	73.95	43.79	32	57	150		N
															509.87	301.9					
BONNET	ASTM A216 WCB-2008	A 12416	0.210	0.41	0.92	0.024	0.012	0.034	0.099	0.030	0.033	0.008	0.018	0.40	75.40	44.95	27	56	155		N
															519.86	309.9					
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268		N
															708.85	504.9					

**YJ135 / 23**

BODY	ASTM A216 WCB-2008	A 12938	0.210	0.42	0.90	0.025	0.010	0.029	0.060	0.005	0.037	0.005	0.015	0.38	76.56	45.97	26	53	157		N
															527.86	317					
BONNET	ASTM A216 WCB-2008	A 12425	0.220	0.48	0.90	0.026	0.014	0.040	0.093	0.003	0.034	0.008	0.059	0.40	75.98	45.82	26	55	154		N
															523.86	315.9					
WEDGE	ASTM A217 CA15-2007	D 9101	0.10	0.99	0.71	0.026	0.011	0.156	12.90	0.099	0.038				106.14	75.55	20	53	265		N
															731.81	520.9					

**YJ135 / 24**

BODY	ASTM A216 WCB-2008	A 13219	0.210	0.41	0.90	0.022	0.009	0.029	0.058	0.002	0.041	0.004	0.032	0.38	73.23	43.07	32	57	151		N
															504.90	297					
BONNET	ASTM A216 WCB-2008	A 12769	0.200	0.45	0.88	0.028	0.016	0.069	0.098	0.077	0.038	0.007	0.009	0.39	76.42	45.53	26	54	156		N
															526.9	313.9					
WEDGE	ASTM A217 CA15-2007	D 9100	0.11	0.89	0.77	0.028	0.010	0.131	12.80	0.095	0.036				104.26	73.66	20	49	270		N
															718.85	507.9					

**YJ135 / 25**

BODY	ASTM A216 WCB-2008	A 12936	0.220	0.42	0.94	0.025	0.012	0.030	0.082	0.012	0.077	0.005	0.019	0.40	75.40	44.95	26	53	155		N
															519.86	309.9					
BONNET	ASTM A216 WCB-2008	A 12783	0.220	0.41	0.88	0.027	0.016	0.029	0.061	0.002	0.035	0.005	0.009	0.38	76.42	45.53	26	53	155		N
															526.9	313.9					
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268		N
															708.85	504.9					

**YJ135 / 26**

BODY	ASTM A216 WCB-2008	A 12932	0.200	0.40	0.87	0.026	0.011	0.024	0.065	0.001	0.034	0.009	0.01	0.36	76.42	45.53	26	53	154		N
															526.9	313.9					
BONNET	ASTM A216 WCB-2008	A 12771	0.200	0.44	0.91	0.028	0.018	0.028	0.056	0.005	0.031	0.003	0.045	0.37	76.56	45.97	26	52	158		N
															527.86	317					
WEDGE	ASTM A217 CA15-2007	D 9101	0.10	0.99	0.71	0.026	0.011	0.156	12.90	0.099	0.038				106.14	75.55	20	53	265		N
															731.81	520.9					

**YJ135 / 27**

BODY	ASTM A216 WCB-2008	A 12938	0.210	0.42	0.90	0.025	0.010	0.029	0.060	0.005	0.037	0.005	0.015	0.38	76.56	45.97	26	53	157		N
															527.86	317					
BONNET	ASTM A216 WCB-2008	A 12770	0.210	0.45	0.93	0.033	0.016	0.032	0.088	0.008	0.029	0.004	0.013	0.39	74.68	44.37	31	56	151		N
															514.90	305.9					

WEDGE	ASTM A217 CA15-2007	D 9101	0.10	0.99	0.71	0.026	0.011	0.156	12.90	0.099	0.038			106.14	75.55	20	53	265		N
														731.81	520.9					

**YJ135 / 28**

BODY	ASTM A216 WCB-2008	A 12934	0.210	0.41	0.88	0.026	0.015	0.031	0.058	0.003	0.026	0.004	0.056	0.37	72.50	43.21	32	57	149		N
															499.87	297.9					
BONNET	ASTM A216 WCB-2008	A 12785	0.200	0.46	0.90	0.026	0.015	0.025	0.066	0.002	0.029	0.005	0.041	0.37	75.40	44.95	27	56	152		N
															519.86	309.9					
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268		N
															708.85	504.9					

**YJ135 / 29**

BODY	ASTM A216 WCB-2008	V 14461	0.221	0.507	0.811	0.018	0.014	0.030	0.035	0.004	0.022	0.002	0.032	0.37	80.48	49.30	31	57	154		N
															554.89	339.9					
BONNET	ASTM A216 WCB-2008	V 14614	0.166	0.409	0.842	0.019	0.008	0.048	0.037	0.002	0.029	0.004	0.035	0.32	70.33	42.05	31	48	142		N
															484.91	289.9					
WEDGE	ASTM A217 CA15-2007	D 9101	0.10	0.99	0.71	0.026	0.011	0.156	12.90	0.099	0.038				106.14	75.55	20	53	265		N
															731.81	520.9					

**YJ135 / 30**

BODY	ASTM A216 WCB-2008	A 13218	0.200	0.45	0.97	0.024	0.012	0.051	0.078	0.005	0.036	0.009	0.014	0.39	76.42	45.39	26	53	155		N
															526.9	313					
BONNET	ASTM A216 WCB-2008	A 12782	0.210	0.48	0.98	0.028	0.016	0.072	0.098	0.014	0.038	0.005	0.049	0.40	74.97	44.81	30	56	152		N
															516.9	309					
WEDGE	ASTM A217 CA15-2007	D 9101	0.10	0.99	0.71	0.026	0.011	0.156	12.90	0.099	0.038				106.14	75.55	20	53	265		N
															731.81	520.9					

**YJ135 / 31**

BODY	ASTM A216 WCB-2008	A 13216	0.210	0.46	0.91	0.025	0.012	0.033	0.074	0.006	0.036	0.005	0.018	0.38	73.23	43.50	30	55	153		N
															504.90	299.9					
BONNET	ASTM A216 WCB-2008	A 12787	0.210	0.42	0.90	0.030	0.014	0.030	0.061	0.004	0.037	0.005	0.014	0.38	72.79	43.21	33	58	149		N
															501.87	297.9					
WEDGE	ASTM A217 CA15-2007	D 9102	0.11	0.93	0.73	0.026	0.010	0.140	12.47	0.091	0.013				102.81	73.23	19	49	268		N
															708.85	504.9					

**YJ135 / 32**

BODY	ASTM A216 WCB-2008	A 12932	0.200	0.40	0.87	0.026	0.011	0.024	0.065	0.001	0.034	0.009	0.01	0.36	76.42	45.53	26	53	154		N
															526.9	313.9					
BONNET	ASTM A216 WCB-2008	A 12425	0.220	0.48	0.90	0.026	0.014	0.040	0.093	0.003	0.034	0.008	0.059	0.40	75.98	45.82	26	55	154		N
															523.86	315.9					
WEDGE	ASTM A217 CA15-2007	D 9101	0.10	0.99	0.71	0.026	0.011	0.156	12.90	0.099	0.038				106.14	75.55	20	53	265		N
															731.81	520.9					

**Heat Treatment Codes:**

<i>A</i> : Annealing	<i>AC</i> : Air Cooling	<i>DA</i> : Double Aged	<i>FT</i> : Furnace Treatment	<i>N</i> : Normalizing	<i>OQ</i> : OilQuenched
<i>Ph-3</i> : Precipitation Hardening	<i>SA</i> : Solution Annealed	<i>SQ</i> : Solution Quenched	<i>ST</i> : Solution Treatment	<i>T</i> : Tempering	<i>WC</i> : Water Cooling
<i>WQ</i> : Water Quenched	<i>WT</i> : Water Quenched/ Tempered			<i>NT</i> : Normalized/Tempered	

Part	Material
BACK SEAT	ASTM A276 410
BODY/BONNET	ASTM A216 WCB
BOLTING	ASTM A193 B7 / ASTM A194 2H
DISC-WEDGE-CLAPPER	ASTM A217 CA15
PACKING	GRAPHITE
SEAT RING	ASTM A105 + Stl.6 Faced
STEM	ASTM A182 F6A Cl. 3
STEM NUT	ASTM A439-D2

Valves Tested per API598  
We hereby certify, that the material described above complies with the order requirements.

**EC Declaration of Conformity: JEV (Jiangyin Eastern Valve Co. Ltd.), Jiangsu Province, 214423, P.R. China**

According to Annex VII of Pressure Equipment Directive 97/23/EC, hereby declare that the products detailed above are in compliance with PED 97/23/EC and have been manufactured in accordance with conformity assessment module B+D as approved Det Norske Veritas Inspection AB as Identification No 0575 (formally 0409). The products may cover Category I, II and III of pressure equipment. For the most specific risks of this equipment, safety and compliance with essential requirements of the Directive has been based on API 600, API598, ASME B16.34, ASME B16.5, ASME B16.10 latest edition.

Undersigned by Liu Jian Qing, representing Jiangyin Eastern Valve company Ltd. :  
