



PROCARSA, S.A. DE C.V.

ETRO : 12 3/4" ESPESOR DE PARED
 WOOD BRIDGE WALL THICKNESS

PRUEBAS DE TENSION
 TENSILE TEST

PROBETA RIPTION	COLADA HEAT	LMITE ELASTICO YIELD STRENGTH (F.S.I.)	ULTIMA TENSION TENSILE STRENGTH (F.S.I.)
4-8 TC TS	170442	51 162	65 434 67 481
5-15 TC TS	180752	48 987	62 648 68 960
1-29 TC TS	180753	51 020	65 439 68 678
2-8TC TS	180754	50 417	62 710 68 694
9-24 TC TS	252103	65 029	77 482 82 774
4-8 TC TS	280724	51 347	63 264 69 218
12-9 TC TS	280725	50 610	65 766 69 177
4-26 TC TS	280726	52 307	63 184 69 928
4-5 TC TS	720128	55 115	71 649 78 658

CONFIRMAMOS QUE LA TUBERIA AQUÍ DESCRITA CUMPLE Y HA SIDO
 VERIFICADA, MUESTREADA, PROBADA E INSPECCIONADA DE ACORDO
 CON LOS REQUISITOS APLICABLES DE LA ESPECIFICACION:

ASTM A53-B -06