

www.smt.sandvik.com www.smt.sandvik.com/nafta

Sandvik Materials Technology

Product Area Tube P.O. Box 1220 Scranton PA USA 18501 570-585-7500

200921109

Page 1

Sold To: 632580 Ship To:

SANDVIK DE MEXICO GAISA FORWARDING INC

TLALNEPANTLA, EDO MEXICO LAREDO TX

Certification Date: 20090707 Customer Order No: 450882

Sandvik Order No: 79786/3 Work Order/Lot: 525343

ASTM A312-08a, ASME SA-312, ASTM A376-06, ASME SA-376, ASME Section II 2007 Edition, 2008 Addenda, NACE MR0175 / ISO 15156

First edition 2003-12-15, (Austenitic)

Hot Finished PROCESS ANNEALED AND PICKLED Seamless Pipe

1" SCH 40 Type TP304/TP304L (UNS S30400/S30403) Size:

Heat:

Material Manufacturer: Pennsylvania Extruded Tube Co. USA ANALYSIS %

Νi CrC Si Mn S 18.39 10.17 .025 .008 .007 1.30 .42 Heat 18.34 10.39 .010 .45 1.29 .027 Prod .009 Mo Al Pb Fе

.003 .31 Heat .31 .003 Prod

Mechanical Tests:

Tensile Reduction Yield Strength Elongation Of Area in % 1.0% Strength 0.2% ક્ષ E2" E10" E5d psi E4dMPa psi MPa MPa psi N/A 565.5 N/AN/A 82000 61 N/A 33000 227.6 N/A

Hardness Test Results: 82HRB, 82HRB

Hydrostatic Test (psi): 2500

Flattening Test per ASTM A999: Acceptable

Tensile Test sample width (1=Full-Size 2=1/2" Strip): 2

Corrosion Test per ASTM A262 Pr.E: Acceptable Country Of Origin: United States

This Material complies with FAR BAA (FAR 52.225-1)

This Material complies with DFARS BAA (DFARS 252.225-7001)

and FAR TAA(FAR 52.225-5)

All material subjected to a final solution annealing heat treatment with material at a temperature of 1900 deg. F

minimum followed by rapid quenching.

The material has not come in contact with Mercury or Mercury

containing compounds.

No welding has been performed on this material.

Material has been manufactured/supplied in accordance

with Sandvik Materials Technology Quality Manual-Standard Products Revision 10 dated May 29, 2007. Quality system has been approved to ISO 9001:2000.

Certificate produced in accordance with EN 10204 3 ANAHUACY CIAS. S.A. DE C.N. (formerly EN 10204 3.1.B)
Melt Source: AB Sandvik MT. Sweden

Melt Method: Electric Arc Furnace-AOD Refinang

are correct and accurate as contained in Sandvik's records, the 2010

Page 2

and that all above test results and operations performed are in compliance with the requirements of the purchase order and the specification(s) listed above.

Electronically Generated Certificate-Valid without signature Audrey Kakareka, Quality Engr. 10 (STKA312/376 R28) (32) (DP)