PAGE : 1 / 1

증명서번호
CERTIFICATE NO.: E201106-0158-001441(5006702)

제 품 명
COMMODITY : E.R.W STEEL PIPE

제 품 규 격
SPECIFICATION : API 5L B(PSL1)

# INSPECTION CERTIFICATE

**SeAH Steel Corp.**

**(주)세 아 제 강**

HEAD OFFICE ; BONGNAE-DONG 1GA, JUNG-GU, SEOUL, KOREA
POHANG PLANT ; 14-1, JANGHEUNG-DONG, NAM-GU, POHANG

발 급 일 자
DATE OF ISSUE : 2011.05.31

계 약 서 번 호
L/C No. (P/O No.) : P01103087278

수 요 가
CUSTOMER : PLESA

주 문 자
SHIPPER : DUFERCO SA

| NO. | HEAT NO. (BATCH NO.) | 관 단 TYPE *1 | 주 문 치 수 ORDER SIZE | 수 량 QUANTITY 본 수 PCS | 총 길 이 TOTAL LENGTH | 중량(M/T) WEIGHT | 비 고 REMARK |
|---|---|---|---|---|---|---|---|
| 1 | KA0963 (SHL5272040) | BBE | 10 " X 0.250 " X 6.120 M | 10 | 61.200 M | 2.576 | |

| NO. | HEAT NO (BATCH NO.) | HYDROSTATIC TEST 5 Sec. psi | RESULT | N·D·T U *2 | VISUAL & DIMENSION | FLATTENING | SHOCK | COMPRESSION | RESIDUAL MAGNETISM GAUSS | BENDING *3 | DRIFT | CRUSH | FLARING | FLANGE | REVERSE FLATTENING |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| 기준 SPEC | | | | | | | | | 30 | | | | | | |
| 1 | KA0963 (SHL5272040) | 1000 | G | G | G | G | | | G | | | | | | |

| NO. | HEAT NO (BATCH NO.) | ZINC COATING TEST WEIGHT OF ZINC COAT-ING | 균일성 C.S *4 | 알칼리 ALK *5 | CHEMICAL COMPOSITION(%) DESIG *6 | C | Si | Mn | P | S | Cu | Ni | Cr | Mo | V | Nb | Ti | | CEQ *8 | DIR *9 | TENSILE TEST (Gage Length : 50mm) TENSILE STRENGTH psi | YIELD STRENGTH psi | E.L % *10 | IMPACT TEST (℃) ENERGY Joule | SHEAR AREA % | HARDNESS TEST | HEAT TREATMENT SN *11 |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | | | | | 2 | | | 3 | | 2 | 2 | 2 | 2 | 3 | 3 | 3 | | | | | | | | | | |
| 기준 SPEC | | | | | MAX | 26 | | 120 | 30 | 30 | 50 | 50 | 50 | 15 | | | | | | | | | | | | | |
| | | | | | MIN | | | | | | | | | | | | | | | | 60200 | 35500 | | | | | |
| 1 | KA0963 (SHL5272040) | | | | H | 16 | 2 | 81 | 17 | 5 | | | | | | | | | | | | | | | | | |
| | | | | | P | 15 | 2 | 81 | 18 | 4 | 1 | TR | TR | TR | 1 | 1 | 1 | | | T | 72950 | 61870 | 31 | | | | G |
| | | | | | P | 16 | 3 | 80 | 19 | 3 | 1 | TR | TR | TR | 1 | 1 | 1 | | | W | 75950 | | | | | | |

NOTE *1 ~ *11: Refer To Others

OTHERS
*1-BBE:Black Beveled End(30°)
*2-U:Weld Seam Ultrasonic Test
*6-H:Heat(Ladle) Analysis, P:Product Analysis *7-2:X100, 3:X1000
*9-T:Base Metal Transverse, W:Weld Part Transverse *10-E.L:Elongation *11-S.N:Seam Normalizing *G:GOOD *Tr:Trace

Surveyor :

- WE HEREBY CERTIFY THAT THE MATERIAL HEREIN HAS BEEN MADE AND TESTED IN ACCORDANCE WITH ABOVE SPECIFICATION AND THE RESULTS OF ALL TEST ARE ACCEPTABLE.
- THE USE OF THE MATERIAL OUTSIDE THE SPECIFICATIONS INDICATED ON THIS CERTIFICATE MAY CAUSE SAFETY AND/OR MONETARY PROBLEMS. FURTHERMORE, ANY ORGANIZATION OR PERSON(S) WHO DELIBERATELY MODIFIES THE CERTIFICATE WILL BE PROSECUTED FOR FORGING AN OFFICIAL DOCUMENT (ACCORDING TO THE PROVISIONS OF THE CRIMINAL CODE 231)

Manager of Q.M Dept.

N. J. Baek

주식회사세아제강 SeAH 품질경영팀장