


CERTIFICADO DE CALIDAD INSPECTION CERTIFICATE (DIN EN 10204:2004E - ISO 10474 3.1.B)	Numero: Number:	Pagina/Page:	
	22135	1 DE 1	

Vendido a: Sold to:	PLESA ANAHUAC Y CIA. S.A. DE C.V.	Pedido del Cliente No: Customers Order No:	5791 -	Lista de Empaque: Packing List:	11264	Fecha/Date:	6 de Febrero de 2009
Especificaciones y Grados / Standard or Specification and Steel Grade Seamless Fittings according to ASTM A 234M WPB-07, NACE MR 01.75-2003 Conform to ASME II Ed. 2001 ASME SA-234M Grade WPB, NACE MR0103-2003		Dimensiones y tolerancias / Dimension and tolerances ASME B 16.9 - 2007 and ASME B 16.28 - 1994		Factura/Invoice: Bocas / Ends Biselado / Bevelled ends			

DESCRIPCION DE MATERIAL / MATERIAL DESCRIPTION				PRUEBAS MECANICAS / MECHANICAL TEST				PRUEBA DE IMPACTO 0°C / IMPACT TEST 0°C				
ART. ITEM	COLADA HEAT CODE	CANTIDAD QUANTITY	DESCRIPCION / DESCRIPTION	ESF. CEDENCIA YIELD STRENGTH (Mpa)	ESF. RUPTURA TENSILE STRENGTH (Mpa)	ELONG. %2"	DUREZA HARDNESS HBW	DIMENSIONES SAMPLE DIM mm	1 Joules	2 Joules	3 Joules	PROMEDIO AVERAGE Joules
23	T23622	4	TEE 5 CED-STD	301	473	36	103					

ANALISIS QUIMICO / CHEMICAL ANALYSIS														Certificamos que los resultados de los Analisis Quimicos y Pruebas Mecanicas son verdaderos o una copia fiel de los certificados enviados por el Fabricante y/o el proveedor de Materia Prima (Tuberia Sin Costura) conforme ASTM A106 Grado B con N°: We certify that result of chemical analysis and mechanical test are true and correct copy of the test certificate issued by the manufacturer and/or supplier Raw material (Seamless Pipe) certs conform to ASTM A106 Grade B N°: 5020390 *Este material cumple con los requerimientos especificados en la orden". *The material of this certificate heat number mentioned above is in compliance with the requirements specified in the order".
PROCESO PROCESS	COLADA HEAT CODE	COLADA/HEAT M.P./MOTHER PIPE	%C.E.	%C	%Mn	%P	%S	%Si	%Cr	%Cu	%Mo	%Ni	%V	
HF	T23622	23622	0.300	0.170	0.670	0.009	0.004	0.300	0.040	0.064	0.044	0.030	0.000	0.000

Notas: Formado en caliente a 620°C-980°C, enfriado al aire; Formado en frío normalizado a 940°C max. Tiempo de permanencia 10'. Inspección Dimensional: Satisfactoria. HF: FORMADO EN CALIENTE/HOT FORMED	Notes: Hot formed fittings in a range from 620°C to 980°C, cooled in still air, Cold formed normalized at 940°C max. Holding time 10'. Visual dimensional check: Satisfactory CF: FORMADO EN FRIO/COLD FORMED	 Quality Manager/Jefe de Calidad: ING. WALDO GALLEGOS GALVAN	The Products described herein were produced in accordance with the above referenced specification and are identified with the "R" which is permanently marked on each fitting./ The values of hardness for fittings NPS 2 1/2" and smaller ones obtain from the conversion of hardness Rockwell B to hardness Brinell HBW by means of table WILSON DESK CHART 60. Los valores de dureza para conexiones de NPS de 2 1/2" y menores, se obtienen de la conversión de dureza Rockwell B a dureza Brinell HBW mediante la tabla WILSON DESK CHART 60.
--	--	--	---