

<b>CERTIFICADO DE CALIDAD</b> <b>INSPECTION CERTIFICATE</b> ( DIN EN 10204:2004E - ISO 10474 3.1.B )	Número: Number:	Página/Page:
	22733	1 DE 1

Vendido a: Sold to:	PLESA ANAHUAC Y CIA. S.A. DE C.V.	Pedido del Cliente No: Customers Order No:	6857 -	Lista de Empaque: Packing List:	11591	Fecha/Date:	26 de Agosto de 2009
Especificaciones y Grados / Standard or Specification and Steel Grade Seamless Fittings according to ASTM A 234M WPB-07, NACE MR 01.75-2003 Conform to ASME II Ed. 2001 ASME SA-234M Grade WPB, NACE MR0103-2003		Dimensiones y tolerancias / Dimension and tolerances <b>ASME B 16.9 - 2007 and ASME B 16.28 - 1994</b>		Factura/Invoice: <b>Bocas / Ends</b> Biselado / Bevelled ends			

DESCRIPCION DE MATERIAL / MATERIAL DESCRIPTION				PRUEBAS MECANICAS / MECHANICAL TEST				PRUEBA DE IMPACTO 0°C / IMPACT TEST 0°C				
ART. ITEM	COLADA HEAT CODE	CANTIDAD QUANTITY	DESCRIPCION / DESCRIPTION	ESF. CEDENCIA YIELD STRENGTH (Mpa)	ESF. RUPTURA TENSILE STRENGTH (Mpa)	ELONG. %2"	DUREZA HARDNESS HBW	DIMENSIONES SAMPLE DIM mm	1 Joules	2 Joules	3 Joules	PROMEDIO AVERAGE Joules
12	T34881	1	TEE 6 CED-STD	366	499	32	86					
13	T39958	1	TEE 6 CED-STD	315	486	33	136					
14	T41032	8	TEE 6 CED-STD	281	472	40	104					
15	T40571	8	TEE 6 CED-STD	348	496	31	106					
16	T42162	2	TEE 6 CED-STD	241	443	36	115					
17	T41827	1	TEE 6 CED-STD	266	465	36	100					


ANALISIS QUIMICO / CHEMICAL ANALYSIS														
PROCESO PROCESS	COLADA HEAT CODE	COLADA/HEAT M.P./MOTHER PIPE	%C.E.	%C	%Mn	%P	%S	%Si	%Cr	%Cu	%Mo	%Ni	%V	%Nb
HF	T34881	34881	0.300	0.160	0.670	0.010	0.003	0.270	0.060	0.096	0.045	0.040	0.000	0.000
EF	T39958	39958	0.300	0.170	0.670	0.008	0.001	0.260	0.050	0.058	0.007	0.030	0.000	0.000
HL	T41032	41032	0.310	0.180	0.670	0.007	0.001	0.270	0.040	0.064	0.007	0.030	0.000	0.000
HF	T40571	40571	0.300	0.170	0.690	0.009	0.004	0.280	0.050	0.057	0.010	0.030	0.000	0.000
HF	T42162	42162	0.300	0.170	0.670	0.012	0.002	0.280	0.040	0.046	0.008	0.020	0.000	0.000
HF	T41827	41827	0.310	0.170	0.670	0.011	0.001	0.280	0.060	0.065	0.032	0.040	0.000	0.000

Certificamos que los resultados de los Análisis Químicos y Pruebas Mecánicas son verdaderos o una copia fiel de los certificados enviados por el Fabricante y/o el proveedor de Materia Prima (Tubería Sin Costura) conforme ASTM A106 Grado B con N°:

We certify that result of chemical analysis and mechanical test are true and correct copy of the test certificate issued by the manufacturer and/or supplier Raw material (Seamless Pipe) certs conform to ASTM A106 Grade B N°:

7037526 8037437 8050797 8038616 9002593 8059867

"Este material cumple con los requerimientos especificados en la orden".  
The material of this certificate heat number mentioned above is in compliance with the requirements specified in the order".

Notas: Formado en caliente a 620°C-980°C, enfriado al aire; Formado en frío normalizado a 940°C max. Tiempo de permanencia 10'. Inspección Dimensional: Satisfactoria. HF: FORMADO EN CALIENTE/HOT FORMED	Notes: Hot formed fittings in a range from 620°C to 980°C, cooled in still air, Cold formed normalized at 940°C max. Holding time 10'. Visual dimensional check: Satisfactory CF: FORMADO EN FRIO/COLD FORMED	<div style="text-align: right;">   <b>Quality Manager / Jefe de Calidad:</b>  <b>ING. WALDO GALLEGOS GALVAN</b> </div>
---	---	--

The Products described herein were produced in accordance with the above referenced specification and are identified with the "R" which is permanently marked on each fitting. / The values of hardness for fittings NPS 2 1/2" and smaller ones obtain from the conversion of hardness Rockwell B to hardness Brinell HBW by means of table WILSON DESK CHART 60.

Los valores de dureza para conexiones de NPS de 2 1/2" y menores, se obtienen de la conversión de dureza Rockwell B a dureza Brinell HBW mediante la tabla WILSON DESK CHART 60.