

PONSOTHER NEEDS SINCE 2, SAUG 16/L TEE

22 Readington Rd, North Branch, NJ 08876
Tel: 908-722-1313; Toll Free: 1-800-223-1068; Fax: 908-722-2943

Material Test Report

105424



Page 33 of 37

Shipment No: 0000049879

Sold To: GLOBAL STAINLESS SUPPLY, INC 8900 RAILWOOD DRIVE SUITE A HOUSTON TX - 77078

Customer PO Number: 10510

TFS Sales Order: 23903X

Item ID: 19808

Item Desc: 2 TEE 40S WP316/316LS A/SA403

Mill Heat: 3186 Heat Code: NHDS Quantity: 41.00 Ship To: GLOBAL STAINLESS SUPPLY, INC 8900 RAILWOOD DRIVE SUITE A HOUSTON TX - 77078

Chemical Properties

C (%)	Cr (%)	Mn (%)	Mo (%)	Ni (%)	P (%)	S (%)	Si (%)
0.019	16.22	0.91	2.03	10.07	0.037	0.002	0.42

Physical Properties

EL (%)	TS (PSI)	YS (PSI)
46	81946	38435

Notes:

ASTM A403-11/ASME SA403 2010 EDITION 2011a ADDENDA

FITTINGS WERE SOLUTION ANNEALED @ 1900 DEG F MINIMUM AND WATER QUENCHED.

NACE MR0103-2010 & MR 0175 / ISO 15156-3:2003, 2007Addenda Compliant-Hardness <RC22

MADE IN USA

EN 10204:2004/3.1

FITTINGS WERE MANUFACTURED, SAMPLED, TESTED AND INSPECTED IN ACCORDANCE WITH

THE SPECIFICATION AND FOUND TO MEET THE REQUIREMENTS.

NO MERCURY, HALOGEN AND LOW MELTING POINT ALLOY CONTAMINATION.

MARKING MATERIALS DO NOT CONTAIN HARMFUL AMOUNTS OF CHLORIDES, METALS OR

METALLIC SALTS SUCH AS ZINC OR COPPER.

ASME B16.9

ISO9001:2008 QUALITY SYSTEM, CERTIFICATE#111144.01, EXPIRATION 9/14/2013.

S. H. Shanty fr.

Stanley Grant QA Assistant Manager 431

12/21/2012