

CERTIFIED MATERIAL TEST REPORT  
Hackney Ladish Inc.

708 South Elmira Avenue - Russellville, AR 72802  
Phone: (800) 527-4500 Fax: (479) 964-6231

Heat Code Description / Specifications

EK97AAB TAP-CS-16C20 A/SA 234 - 96A WPB (SMLS)  
A516-70 TUSCAL/A7U2079 NORM. 1650 NACE MR0175

Chemical Analysis

<u>Heat Code</u>	<u>Test</u>	<u>C</u>	<u>Mn</u>	<u>P</u>	<u>S</u>	<u>Si</u>	<u>Cu</u>	<u>Ni</u>	<u>Cr</u>	<u>Mo</u>	<u>Al</u>
EK97AAB	M	.230	1.050	.010	.003	.220	.100	.040	.030	.000	.0038

Chemical Analysis (cont.)

<u>Heat Code</u>	<u>N</u>	<u>V</u>	<u>B</u>	<u>Ti</u>	<u>Cb</u>	<u>Sn</u>	<u>W</u>	<u>Pb</u>	<u>Co</u>	<u>CE</u>
EK97AAB	.0005	.003		.0002	.003					.420

Physical Properties

<u>Heat Code</u>	<u>Tensile KSI</u>	<u>Type</u>	<u>Thickness</u>	<u>Yield KSI</u>	<u>% Elong. (4D)</u>	<u>% RA</u>	<u>Hardness HB</u>
EK97AAB	81.6	T		54.9	29.0		150

Charpy Results

<u>Heat Code</u>	<u>Size x 10mm</u>	<u>Type</u>	<u>Temp. (F)</u>	<u>Foot Pounds</u>	<u>Later. Expansion</u>	<u>% Shear</u>
EK97AAB						

Test: M=Mill Product  
Type: T=Transverse

We certify that the material herein described has been manufactured in accordance with the above standards and specifications and satisfies all the requirements of the editions specified. We certify all materials provided comply with ISO 10204 paragraph. 3.1 which replaces type 3.1.B of the 1991 edition of EN 10204. Our ISO 9001:2008 certificate number is CERT-11763-2007-USA-RvA/ANAB. We certify these fittings capable of passing hydrostatic test compatible with their rating. The above figures are correct as contained in the records of the Company. This information has been electronically transmitted to our customer.