

CERTIFIED MATERIAL TEST REPORT
Hackney Ladish Inc.

P.O. Box 803466 - 5495 Beltline Rd. #290 - Dallas, TX 75254
Phone: (800) 527-4500 Fax: (214) 269-5601

Heat Code Description / Specifications

EM01FO	T-RECS-18-STD	A/SA 234 - 00	WPB (SMLS)
	A106-B 9/B09834	NORM. 1650	NACE MR0175

Chemical Analysis

Heat Code	Test	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al
EM01FO	M	.180	1.080	.007	.007	.210	.010	.020	.050	.030	.0280

Chemical Analysis (cont.)

Heat Code	N	V	B	Ti	Cb	Sn	W	Pb	Co	CE
EM01FO	.0050	.010	.0005	.0100	.010	.002	.002	.002	.050	.380

Physical Properties

Heat Code	Tensile KSI	Type	Thickness	Yield KSI	% Elong. (4D)	% RA	Hardness HB
EM01FO	77.8	L		51.8	34.0	72.0	140

Charpy Results

Heat Code	Size x 10mm	Type	Temp. (F)	Foot Pounds	Later. Expansion	% Shear
EM01FO						

Test: M=Mill Product
Type: L=Longitudinal

We certify that the material herein described has been manufactured in accordance with the above standards and specifications and satisfies all the requirements of the editions specified. We certify all materials provided comply with ISO 10204 paragraph. 3.1 which replaces type 3.1.B of the 1991 edition of EN 10204. Our ISO9001:2000 certificate number is CERT11763-2007-AQ-HOU-RVA/ANAB. We certify these fittings capable of passing hydrostatic test compatible with their rating. The above figures are correct as contained in the records of the Company. This information has been electronically transmitted to our customer.