

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS:
(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES)

- | | | | |
|-------------|---|-------------|---|
| API 598 | - VALVE INSPECTION AND TESTING | API 6D | - PIPELINE VALVES - GATE, PLUG, BALL ANF CHECK |
| API 599 | - METAL PLUG VALVES - FLANGED, THREADED AND WELDING | API 600 | - STEEL GATE VALVES, FLANGED AND WELDING ENDS |
| ANSI B16-10 | - FACE TO FACE AND END TO END DIMENSIONS OF VALVES | ANSI B16-11 | - FORGED FITTINGS, SOCKET - WELDING AND THREADED |
| ANSI B16-34 | - VALVES - FLANGED, THREADED AND WELDING ENDS | API 602 | - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS |
| MSS-SP61 | - PRESSURE TESTING OF STEEL VALVES | | |

Part No. **AC032A08MAA**

(Codigo) **3" Fig. 5206 F UT WCB, API TRIM No.8 8300000**

Description **CAST STEEL GATE VALVE**

(VALVULA COMPUERTA DE ACERO FUNDIDO)
VALVE WITH LOW EMISSION CONTROL
(VALVULA SUMINISTRADA CON CONTROL DE EMISIONES FUGITIVAS A 50 PPM'S MAX)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)
HYDROSTATIC (PSI) (HIDROSTATICA)	1125	1125	N A N A
PNEUMATIC (PSI) (NEUMATICA)			80 80

CHEMICAL COMPOSITION (%)

COMPOSICIÓN QUÍMICA (%)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	W	TENS (KPSI CVN ₅₀)	YIELD (KPSI 1ST)	ELG (% 2ND)	RED (% 3RD)	BHN (AVG)
BONNET BONETE	WH16637	ASTM A-216/WCB	0.216	0.983	0.025	0.014	0.450	0.053	0.173	0.024	0.037	0.006		78.01	49.01	32	47	152
BODY CUERPO	WH16702	ASTM A-216/WCB	0.194	0.900	0.022	0.012	Tempor to (Temple a) 650 °C 0.551	0.052	0.074	0.022	0.047	0.006		73.08	41.47	37	58	150
WEDGE DISCO	WH81112	ASTM A-217/CA15	0.135	0.793	0.021	0.027	0.674	0.114	13.310	0.026	0.015	0.001	0.000	102.66	72.94	26	48	287
			Normalizado a (Normalizado to) 970 °C				Temple a (Temple to) 630 °C				Enfriado en aire. (Enfriado en aire. (C))							

MECHANICAL TESTS (PROP. MECANICAS)