

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS:
 (CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES.)

- | | | | |
|-------------|---|-------------|---|
| API 598 | - VALVE INSPECTION AND TESTING | API 6D | - PIPELINE VALVES - GATE, PLUG, BALL ANF CHECK |
| API 599 | - METAL PLUG VALVES - FLANGED, THREADED AND WELDING | API 600 | - STEEL GATE VALVES, FLANGED AND WELDING ENDS |
| ANSI B16-10 | - FACE TO FACE AND END TO END DIMENSIONS OF VALVES | ANSI B16-11 | - FORGED FITTINGS, SOCKET - WELDING AND THREADED |
| ANSI B16-34 | - VALVES - FLANGED, THREADED AND WELDING ENDS | API 602 | - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS |
| MSS-SP61 | - PRESSURE TESTING OF STEEL VALVES | | |

Part No. AC041A08MAA

(Codigo) 4" Fig. 5202 F UT WCB, API TRIM No.8 8300000

Description CAST STEEL GATE VALVE
 (VALVULA COMPUERTA DE ACERO FUNDIDO)
 VALVE WITH LOW EMISSION CONTROL.
 (VALVULA SUMINISTRADA CON CONTROL DE EMISIONES FUGITIVAS A 50 PPM'S MAX)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE 1	(LADO) 2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N/A	N/A
PNEUMATIC (PSI) (NEUMATICA)			80	80

CHEMICAL COMPOSITION (%)

COMPOSICIÓN QUÍMICA (%)

ITEM (PARTES)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	W	TENS KPSI CVN/6	YIELD KPSI 1ST	ELG %	RED %	BHN AVG
BONNET	WH23607	ASTM A-216/WCB	0.196	0.910	0.027	0.021	0.493	0.057	0.040	0.024	0.028	0.007		76.70	46.11	34	47	151
BONNETE			Normalized to (Normalized a) 930 °C															
BODY	WH23603	ASTM A-216/WCB	0.215	0.873	0.026	0.015	0.492	0.012	0.014	0.024	0.043	0.004		83.67	47.13	30	52	160
CUERPO			Normalized to (Normalizado a) 930 °C															
WEDGE	WH81104	ASTM A-217/CA15	0.139	0.631	0.034	0.024	0.621	0.089	12.790	0.020	0.019	0.001	0.000	91.20	71.63	28	257	280
DISCO			Normalized a (Normalizado to) 970 °C															
			Temple a (Temper to) 630 °C															

MECHANICAL TESTS (PROP. MECANICAS)