



**WALWORTH**  
Since 1842

Industrial de Valvulas, S.A de C.V.  
Av. de La Industria Lote 16 Fracc. Industrial El Trebol  
Tepic, Jalisco, Estado de Mexico C.P. 54600

(Numero) Number  
(Fecha) Date

V07C33288  
26/10/2007

## QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

### ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS:  
(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES.)

- API 598 - VALVE INSPECTION AND TESTING
- API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING
- ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES
- ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS
- MSS-SP61 - PRESSURE TESTING OF STEEL VALVES
- API 6D - PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
- API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS
- ANSI B16-11 - FORGED FITTINGS, SOCKET - WELDING AND THREADED
- API 602 - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. **AC061A12MAB**

(Codigo) **6" Fig. 5202 F 3HF WCB, API TRIM No.12 790000M**

Description **CAST STEEL GATE VALVE (VALVULA COMPUERTA DE ACERO FUNDIDO)**  
MANUFACTURED TO MEET NACE MR-01-75-2003 REQUIREMENTS AND LOW FUGITIVE EMISSIONS CONTROL.  
(VALVULA SERVICIO NACE MR-01-75 -Y CONTROL DE EMISIONES FUGITIVAS 50 PPM'S)

TEST	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
PRESSURE TEST (PRUEBAS DE PRESION)	450	450	1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N/A	N/A
PNEUMATIC (PSI) (NEUMATICA)			80	80

### CHEMICAL COMPOSITION (%)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	W	COMPOSICIÓN QUÍMICA (%)				
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001		TENS	YIELD	ELG	RED	BHN
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001		KPSI	KPSI	%	%	AVG
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001		CVN <sub>50</sub>	1ST	2ND	3RD	
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB	0.213	0.910	0.018	0.014	0.478	0.052	0.060	0.007	0.009	0.001						
BONNET	WH19194	ASTM A-216/WCB																