



Industrial de Valvulas, S.A de C.V.  
 Av. de La Industria Lote 16 Fracc. Industrial El Trebol  
 Tepozotlan, Estado de México C.P. 54600

(Numero) Number V07C37882  
 (Fecha) Date 10/12/2007

## QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

### ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS:  
 (CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES.)

- API 598 - VALVE INSPECTION AND TESTING
- API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING
- ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES
- ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS
- MSS-SP61 - PRESSURE TESTING OF STEEL VALVES
- API 6D - PIPELINE VALVES - GATE, PLUG, BALL ANF CHECK
- API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS
- ANSI B16-11 - FORGED FITTINGS, SOCKET - WELDING AND THREADED
- API 602 - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. AC011A08MAB

(Codigo) 2" Fig. 5202 F UT WCB, API TRIM No.8 830000K

Description CAST STEEL GATE VALVE  
 (VALVULA COMPUERTA DE ACERO FUNDIDO)  
 VALVE WITH LOW EMISSION CONTROL  
 (VALVULA SUMINISTRADA CON CONTROL DE EMISIONES FUGITIVAS A 50 PPM'S MAX)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEANT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N A	N A
PNEUMATIC (PSI) (NEUMATICA)			80	80

#### MECHANICAL TESTS (PROP. MECANICAS)

#### CHEMICAL COMPOSITION (%)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	COMPOSICIÓN QUIMICA (%)															
			C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	W	TENS KPSI CVN/60	YIELD KPSI 1ST	ELG %	RED %	BHN AVG
BONNET	WH24916	ASTM A-216/WCB	0.205	0.914	0.035	0.016	0.390	0.006	0.036	0.013	0.024	0.007		71.78	40.17	36	51	153
BONNET	WH24916	ASTM A-216/WCB	Normalized to (Normalized a) 930 °C															
BONNET	WH24916	ASTM A-216/WCB	0.193	0.954	0.018	0.017	0.493	0.034	0.046	0.035	0.033	0.002	0.002	72.36	44.23	28	50	162
BONNET	WH24916	ASTM A-216/WCB	Normalized to (Normalized a) 930 °C															
BONNET	WH24916	ASTM A-216/WCB	0.120	0.780	0.030	0.016	0.890	0.410	12.140	0.010	0.026	0.001		99.91	70.33	26	42	272
BONNET	WH24916	ASTM A-216/WCB	Normalized to (Normalized to) 970 °C															
BONNET	WH24916	ASTM A-216/WCB	Temple a (Temper to) 630 °C															
BONNET	WH24916	ASTM A-216/WCB	Enfriado en aire (Enfriado en aire. (C)															

CERTIFICADO POR:  
 ASEGURAMIENTO DE CALIDAD

CERTIFIED BY:  
 SANDRA RUIZ

QUALITY ASSURANCE