

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)
 ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICION)

- API 598 - VALVE INSPECTION AND TESTING
- API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING
- ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES
- ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS
- MSS-SP61 - PRESSURE TESTING OF STEEL VALVES
- API 6D - PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
- API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS
- ANSI B16-11 - FORGED FITTINGS, SOCKET - WELDING AND THREADED
- API 602 - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. **AC011A08MAB**

(Codigo) **2" Fig. 5202 F UT WCB, API TRIM No.8 830000K**

Description **CAST STEEL GATE VALVE**

(VALVULA COMPUTUERTA DE ACERO FUNDIDO)

VALVE WITH LOW EMISSION CONTROL (VALVULA SUMINISTRADA CON CONTROL DE EMISIONES FUGITIVAS A 50 PPM'S MAX)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N A
PNEUMATIC (PSI) (NEUMATICA)			80

MECHANICAL TESTS (PROP. MECANICAS)

CHEMICAL COMPOSITION (%)

COMPOSICIÓN QUIMICA (%)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	TENS (KPSI CVN@)	YIELD (KPSI 1ST)	ELG (% 2ND)	RED (% 3RD)	BHN (AVG)
BONNET	WH25872	ASTM A-216/WCB	0.196	0.899	0.030	0.016	0.482	0.009	0.050	0.006	0.009	0.004	0.004	75.26	45.26	28	50	156
BONNET	WH26488	ASTM A-216/WCB	0.203	0.925	0.029	0.014	0.490	0.021	0.031	0.005	0.005	0.002	0.002	74.97	45.82	26	47	163
CUERPO	WH26488	ASTM A-216/WCB	0.110	0.780	0.019	0.024	0.960	0.310	12.410	0.038	0.051	0.004	0.004	97.73	70.16	25	45	275

Normalizado a (Normalized a) 930 °C
 Normalizado a (Normalized a) 930 °C
 Normalizado a (Normalized a) 930 °C
 Normalizado a (Normalized a) 970 °C