

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)
ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES

FOLLOWING STANDARDS LAST EDITION:
ESTANDARES ULTIMA EDICION.)

- API 598 - VALVE INSPECTION AND TESTING
- API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING
- ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES
- ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS
- MSS-SP61 - PRESSURE TESTING OF STEEL VALVES
- API 6D - PIPELINE VALVES - GATE, PLUG, BALL ANF CHECK
- API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS
- ANSI B16-11 - FORGED FITTINGS, SOCKET - WELDING AND THREADED
- API 602 - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. **AC011A08MAB**

(Codigo) **2" Fig. 5202 F UT WCB, API TRIM No.8 830000K**

Description **CAST STEEL GATE VALVE**

(VALVULA COMPUTUERA DE ACERO FUNDIDO)

VALVE WITH LOW EMISSION CONTROL. (VALVULA SUMINISTRADA CON CONTROL DE EMISIONES FUGITIVAS A 50 PPM'S MAX)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N A	N A
PNEUMATIC (PSI) (NEUMATICA)			80	80

MECHANICAL TESTS (PROP. MECANICAS)

CHEMICAL COMPOSITION (%)

COMPOSICION QUIMICA (%)

ITEM (PART)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	TENS KPSI CMM/4	YIELD KPSI 1ST	ELG %	RED %	BHN AVG	
BONNET	WH22444	ASTM A-216/WCB	0.191	0.952	0.025	0.014	0.400	0.023	0.050	0.039	0.030	0.001	0.001	72.65	43.36	27	48	158	
BONNET	WH24489	ASTM A-216/WCB	Normalized to (Normalized a) 930 °C 0.215	0.944	0.017	0.021	0.436	0.013	0.025	0.005	0.005	0.001	0.001	76.42	45.82	27	48	164	
CUERPO	D0015	ASTM A-217/CA15	Normalized to (Normalized a) 930 °C 0.100	0.870	0.017	0.025	Temper to (Temper a) 650 °C 0.870	0.210	12.520	0.011	0.065	0.005	0.005	97.44	70.18	25	47	269	
DISCO			Normalized a (Normalized to) 970 °C				Temple a (Temper to) 630 °C												