

## QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)  
**ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO**

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598	- VALVE INSPECTION AND TESTING	API 6D	- PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
API 599	- METAL PLUG VALVES - FLANGED, THREADED AND WELDING	API 600	- STEEL GATE VALVES, FLANGED AND WELDING ENDS
ANSI B16-10	- FACE TO FACE AND END TO END DIMENSIONS OF VALVES	ANSI B16-11	- FORGED FITTINGS, SOCKET - WELDING AND THREADED
ANSI B16-34	- VALVES - FLANGED, THREADED AND WELDING ENDS	API 602	- COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS
MSS-SP61	- PRESSURE TESTING OF STEEL VALVES		

**Part No. AC061A08MAB830000M**  
 (Código) **6" Fig. 5202 F UT WCB, API TRIM No.8 830000M**  
**Description** Description

**CAST STEEL GATE VALVE 150 PSI**  
**(VALVULA COMPUERTA DE ACERO FUNDIDO 150 PSI)**

VALVE WITH LOW EMISSION CONTROL (VALVULA SUMINISTRADA CON CONTROL DE EMISIONES FUGITIVAS A 50 PPM'S MAX )

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N A	N A
PNEUMATIC (PSI) (NEUMATICA)			80	80

**MECHANICAL TESTS** (PROP. MECANICAS)

CHEMICAL COMPOSITION (%)													COMPOSICIÓN QUIMICA (%)					TENS	YIELD	ELG	RED	BHN
ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	KPSI CVN@	KPSI 1ST	% 2ND	% 3RD	AVG				
<b>BODY</b> CUERPO	WH26895	ASTM A-216/WCB	0.215	0.904	0.036	0.042	0.441	0.093	0.070	0.035	0.040	0.001		74.53	43.94	29	49	158				
Normalized to (Normalizado a) 930 °C						Temper to (Temple a) 650 °C			Cooled in air.(Cooled in air. (Enfr)													
<b>BONNET</b> BONETE	WH28646	ASTM A-216/WCB	0.198	0.960	0.023	0.021	0.463	0.007	0.027	0.007	0.026	0.006		82.07	44.66	30	42	159				
Normalized to (Normalizado a) 930 °C						Temper to (Temple a) 650 °C			Cooled in air.(Cooled in air. (Enfr)													
<b>WEDGE</b> DISCO	D4857	ASTM A-217/CA15	0.090	0.870	0.032	0.016	0.940	0.550	12.610	0.041	0.040	0.002		97.30	72.79	27	44	275				
Normalized a (Normalizado to) 970 °C						Temple a (Temper to) 630 °C			Enfriado en aire.(Enfriado en aire. (C)													

FAC10-21 REV "3"

  
**JESSICA GARCIA**