WALWORTH® Since 1842

Industrial de Valvulas, S.A de C.V.
Av. de La Industria Lote 16 Fracc. Industrial El Trebol
Tepotzotlan, Estado de México C.P. 54600

(Numero) Number V09C19986
(Fecha) Date 09/09/2009

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PROBADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598	- VALVE INSPECTION AND TESTING
API 599	- METAL PLUG VALVES - FLANGED, THREADED AND WELDING
ANSI B16-10	- FACE TO FACE AND END TO END DIMENSIONS OF VALVES
ANSI B16-34	- VALVES - FLANGED, THREADED AND WELDING ENDS
MSS-SP61	- PRESSURE TESTING OF STEEL VALVES
API 6D	- PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
API 600	- STEEL GATE VALVES, FLANGED AND WELDING ENDS
ANSI B16-11	- FORGED FITTINGS, SOCKET - WELDING AND THREADED
API 602	- COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. (Código) **AC011A08MAA8300000**

Description Descripción **2" Fig. 5202 F UT WCB, API TRIM No.8 8300000**

CAST STEEL GATE VALVE 150 PSI
(VALVULA COMPUERTA DE ACERO FUNDIDO 150 PSI)

VALVE WITH LOW EMISSION CONTROL (VALVULA SUMINISTRADA CON CONTROL DE EMISIONES FUGITIVAS A 50 PPM'S MAX)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO) 1	SIDE (LADO) 2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N A	N A
PNEUMATIC (PSI) (NEUMATICA)			80	80

CHEMICAL COMPOSITION (%) COMPOSICIÓN QUIMICA (%)

MECHANICAL TESTS (PROP. MECANICAS)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	TENS KPSI CVN@	YIELD KPSI 1ST	ELG % 2ND	RED % 3RD	BHN AVG
BODY CUERPO	WH19613	ASTM A-216/WCB	0.216	0.890	0.017	0.012	0.448	0.046	0.272	0.032	0.005	0.001		78.88	43.94	32	54	156
			Normalizated to (Normalizado a) 920 °C				Temper to (Temple a) 650 °C			Cooled in air.(Cooled in air. (Enfr)								
BONNET BONETE	WH28750	ASTM A-216/WCB	0.187	0.900	0.033	0.012	0.514	0.039	0.025	0.009	0.075	0.002		75.83	48.86	28	46	152
			Normalizated to (Normalizado a) 930 °C				Temper to (Temple a) 650 °C			Cooled in air.(Cooled in air. (Enfr)								
WEDGE DISCO	D3628	ASTM A-217/CA15	0.110	0.740	0.024	0.017	0.920	0.380	12.340	0.032	0.065	0.003		98.31	71.92	28	44	275
			Normalizado a (Normalizated to) 970 °C				Temple a (Temper to) 630 °C			Enfriado en aire.(Enfriado en aire. (C)								

FAC10-21 REV "3"

CERTIFICADO POR:
ASEGURAMIENTO DE CALIDAD

CERTIFIED BY :
QUALITY ASSURANCE

JESSICA GARCIA