

## QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)  
ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598 - VALVE INSPECTION AND TESTING  
API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING  
ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES  
ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS  
MSS-SP61 - PRESSURE TESTING OF STEEL VALVES

API 6D - PIPELINE VALVES - GATE, PLUG, BALL AND CHECK  
API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS  
ANSI B16-11 - FORGED FITTINGS, SOCKET - WELDING AND THREADED  
API 602 - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. **AC081A08MAA8300000**  
(Código) **8" Fig. 5202 F UT WCB, API TRIM No.8 8300000**  
Description **CAST STEEL GATE VALVE 150 PSI**  
Descripción **(VALVULA COMPUERTA DE ACERO FUNDIDO 150 PSI)**

VALVE WITH LOW EMISSION CONTROL (VALVULA SUMINISTRADA CON CONTROL DE EMISIONES FUGITIVAS A 50 PPM'S MAX )

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	315	315
PNEUMATIC (PSI) (NEUMATICA)			80	80

### MECHANICAL TESTS (PROP. MECANICAS)

### CHEMICAL COMPOSITION (%)

### COMPOSICIÓN QUIMICA (%)

### TENS YIELD ELG RED BHN

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	KPSI CVN@	KPSI 1ST	% 2ND	% 3RD	AVG				
<b>BODY</b> CUERPO	WH25575	ASTM A-216/WCB	0.193	0.872	0.026	0.014	0.477	0.020	0.052	0.014	0.020	0.002		73.08	42.63	25	48	152				
			Normalizated to (Normalizado a) 930 °C										Temper to (Temple a) 650 °C					Cooled in air.(Cooled in air. (Enfr)				
<b>BONNET</b> BONETE	WH25094	ASTM A-216/WCB	0.214	0.939	0.031	0.020	0.437	0.032	0.059	0.033	0.023	0.005		74.53	36.25	27	56	151				
			Normalizated to (Normalizado a) 930 °C										Temper to (Temple a) 650 °C					Cooled in air.(Cooled in air. (Enfr)				
<b>WEDGE</b> DISCO	WH81431	ASTM A-217/CA15	0.128	0.742	0.031	0.009	0.604	0.108	13.370	0.019	0.024	0.009		92.08	71.34	35	53	300				
			Normalizado a (Normalizado to) 970 °C										Temple a (Temper to) 630 °C					Enfriado en aire.(Enfriado en aire. (C)				

FAC10-21 REV "3"