

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)
ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRUBADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598 - VALVE INSPECTION AND TESTING
 API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING
 ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES
 ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS
 MSS-SP61 - PRESSURE TESTING OF STEEL VALVES

API 6D - PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
 API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS
 ANSI B16-11 - FORGED FITTINGS, SOCKET - WELDING AND THREADED
 API 602 - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. FS011A1MABV80000Z
 (Código) **2" Fig. 1912 F WCB, V80000Z**
Description CAST STEEL SLAB GATE VALVE (API-6D) 150 PSI
 Descripción (VALVULA COMPUERTA PLANA DE ACERO FUNDIDO (API-6D) 150 PSI)

NACE-MR-01-75, FIRE TEST API 6FA (NORMA NACE-MR-01-75, PRUEBA DE FUEGO API 6FA)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N A	N A
PNEUMATIC (PSI) (NEUMATICA)			80	80

MECHANICAL TESTS (PROP. MECANICAS)

CHEMICAL COMPOSITION (%)			COMPOSICIÓN QUIMICA (%)										TENS	YIELD	ELG	RED	BHN	
ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	KPSI CVN@	KPSI IST	% 2ND	% 3RD	AVG
BODY CUERPO	17908	ASTM A-216/WCB	0.190	0.730	0.021	0.019	0.420	0.064	0.083	0.072	0.077	0.001		76.41	41.03	29	39	162
BONNET BONETE	17518	ASTM A-216/WCB	Normalized to (Normalizado a) 920 °C				Temper to (Temple a) 650 °C			Cooled in air.(Cooled in air. (Enfr)				76.70	741.18	30	40	164
WEDGE DISCO	F9710	ASTM A-515 GR 70	Normalized to (Normalizado a) 920 °C				Temper to (Temple a) 650 °C			Cooled in air.(Cooled in air. (Enfr)				77.43	42.92	24	40	185