

## QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PROBADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

- |             |   |             |   |
|-------------|---|-------------|---|
| API 598     | - VALVE INSPECTION AND TESTING                      | API 6D      | - PIPELINE VALVES - GATE, PLUG, BALL AND CHECK                                    |
| API 599     | - METAL PLUG VALVES - FLANGED, THREADED AND WELDING | API 600     | - STEEL GATE VALVES, FLANGED AND WELDING ENDS                                     |
| ANSI B16-10 | - FACE TO FACE AND END TO END DIMENSIONS OF VALVES  | ANSI B16-11 | - FORGED FITTINGS, SOCKET - WELDING AND THREADED                                  |
| ANSI B16-34 | - VALVES - FLANGED, THREADED AND WELDING ENDS       | API 602     | - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS |
| MSS-SP61    | - PRESSURE TESTING OF STEEL VALVES                  |             |   |

**Part No.** AR031A22MAA8300000  
(Código)  
**Description** 3" Fig. 5341 F AAA WCB, API TRIM No.6 8300000  
Descripción CAST STEEL SWING CHECK VALVE 150 PSI  
(VALVULA RETENCIÓN TIPO COLUMPIO DE ACERO FUNDIDO 150 PSI)

VALVE WITH LOW EMISSION CONTROL (VALVULA SUMINISTRADA CON CONTROL DE EMISIONES FUGITIVAS A 50 PPM'S MAX )

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	N A	315	N A
PNEUMATIC (PSI) (NEUMATICA)			N A	N A

### MECHANICAL TESTS (PROP. MECANICAS)

### CHEMICAL COMPOSITION (%) COMPOSICIÓN QUIMICA (%)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	CHEMICAL COMPOSITION (%)										TENS	YIELD	ELG	RED	BHN			
			C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Ce	KPSI CVN@	KPSI 1ST	% 2ND	% 3RD	AVG		
BODY CUERPO	312932	ASTM A-216/WCB	0.190	0.920	0.010	0.009	0.540	0.021	0.150	0.001	0.000									
			Normalizated to (Normalizado a) 930 °C				Temper to (Temple a) 650 °C				Cooled in air.(Cooled in air. (Enfri				81.55	49.99	27	46	163	
COVER TAPA	41041108	ASTM A-216/WCB	0.180	0.890	0.020	0.007	0.550	0.260	0.080	0.010	0.190	0.000								
			Normalizated to (Normalizado a) 955 °C				Temper to (Temple a) 650 °C				Cooled in air.(Cooled in air. (Enfri				79.00	50.00	35	62	149	
WEDGE DISCO	WH81105	ASTM A-217/CA15	0.136	0.640	0.032	0.021	0.602	0.087	12.810	0.020	0.020	0.001								
			Enfriado en aire.(Enfriado en aire. (C)										92.51	71.92	26	41	257			

FAC10-21 REV "3"