

## QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

### ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598	- VALVE INSPECTION AND TESTING
API 599	- METAL PLUG VALVES - FLANGED, THREADED AND WELDING
ANSI B16-10	- FACE TO FACE AND END TO END DIMENSIONS OF VALVES
ANSI B16-34	- VALVES - FLANGED, THREADED AND WELDING ENDS
MSS-SP61	- PRESSURE TESTING OF STEEL VALVES

API 6D	- PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
API 600	- STEEL GATE VALVES, FLANGED AND WELDING ENDS
ANSI B16-11	- FORGED FITTINGS, SOCKET - WELDING AND THREADED
API 602	- COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

**Part No. AG011A08MAB830000Z**

(Código)

**2" Fig. 5275 F UT WCB, API TRIM No.8 830000**

**Description**

Descripción

**CAST STEEL GLOBE VALVE 150 CLASS  
(VALVULA GLOBO DE ACERO FUNDIDO CLASE 150)**

VALVE MANUFACTURED TO MEET LOW FUGITIVE EMISSION (50 PPM'S MAX) & NACE SERVICE MR-01-75 (VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS 50 PPM'S MAX.) Y PARA SERVICIO NACE MR-01-75 / MR0103-2007)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	315	N A
PNEUMATIC (PSI) (NEUMATICA)			80	N A

#### MECHANICAL TESTS (PROP. MECANICAS)

#### CHEMICAL COMPOSITION (%)

#### COMPOSICIÓN QUIMICA (%)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	TENS	YIELD	ELG	RED	BHN
														KPSI CVN@	KPSI 1ST	% 2ND	% 3RD	AVG
<b>BODY</b>	N3342	ASTM A-216/WCB	0.180	0.720	0.018	0.028	0.360	0.041	0.042	0.007	0.028	0.002		71.63	36.54	23	36	156
CUERPO			Normalized to (Normalizado a) 930 °C				Temper to (Temple a) 650 °C			Cooled in air. (Enfriado en aire.)								
<b>BONNET</b>	N3222	ASTM A-216/WCB	0.210	0.740	0.020	0.029	0.370	0.043	0.044	0.008	0.028	0.003		73.95	36.83	24	40	160
BONETE			Normalized to (Normalizado a) 930 °C				Temper to (Temple a) 650 °C			Cooled in air. (Enfriado en aire.)								
<b>WEDGE</b>	1002125	ASTM A-216/WCB	0.190	0.600	0.020	0.013	0.190	0.040	0.060	0.030	0.060	0.002		70.33	44.95	28	58	156
DISCO			Normalized to (Normalizado a) 930 °C				Temper to (Temple a) 650 °C			Cooled in air. (Enfriado en aire.)								

CERTIFICADO POR:  
ASEGURAMIENTO DE CALIDAD

CERTIFIED BY :  
QUALITY ASSURANCE



Yolanda Ponciano