

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PROBADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598	- VALVE INSPECTION AND TESTING
API 599	- METAL PLUG VALVES - FLANGED, THREADED AND WELDING
ANSI B16-10	- FACE TO FACE AND END TO END DIMENSIONS OF VALVES
ANSI B16-34	- VALVES - FLANGED, THREADED AND WELDING ENDS
MSS-SP61	- PRESSURE TESTING OF STEEL VALVES

API 6D	- PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
API 600	- STEEL GATE VALVES, FLANGED AND WELDING ENDS
ANSI B16-11	- FORGED FITTINGS, SOCKET - WELDING AND THREADED
API 602	- COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. AG012A08MAB830000Z
 (Código) **2" Fig. 5281 F UT WCB, API TRIM No.8 830000**

Description CAST STEEL GLOBE VALVE 300 CLASS
 Descripción (VALVULA GLOBO DE ACERO FUNDIDO CLASE 300)

VALVE MANUFACTURED TO MEET LOW FUGITIVE EMISSION (50 PPM'S MAX) & NACE SERVICE MR-01-75 (VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS 50 PPM'S MAX.) Y PARA SERVICIO NACE MR-01-75 / MR0103-2007)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	1125	1125	815	N A
PNEUMATIC (PSI) (NEUMATICA)			80	N A

MECHANICAL TESTS (PROP. MECANICAS)

CHEMICAL COMPOSITION (%)													COMPOSICIÓN QUIMICA (%)					TENS	YIELD	ELG	RED	BHN
ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	KPSI CVN@	KPSI 1ST	% 2ND	% 3RD	AVG				
BODY	N3303	ASTM A-216/WCB	0.180	0.710	0.018	0.028	0.360	0.041	0.042	0.007	0.027	0.002		71.34	36.40	22	36	156				
CUERPO			Normalized to (Normalizado a) 930 °C						Temper to (Temple a) 650 °C			Cooled in air. (Enfriado en aire.)										
BONNET BONETE	N3253	ASTM A-216/WCB	0.220	0.770	0.021	0.030	0.370	0.046	0.047	0.007	0.030	0.003		73.23	36.83	24	39	160				
WEDGE DISCO	1002125	ASTM A-216/WCB	0.190	0.600	0.020	0.013	0.190	0.040	0.060	0.030	0.060	0.002		70.33	44.95	28	58	156				
			Normalized to (Normalizado a) 930 °C						Temper to (Temple a) 650 °C			Cooled in air. (Enfriado en aire.)										

 CERTIFICADO POR:
 ASEGURAMIENTO DE CALIDAD

 CERTIFIED BY :
 QUALITY ASSURANCE



Yolanda Ponciano