WALWORTH® Since 1842

Industrial de Valvulas, S.A. de C.V.
Av. de La Industria Lote 16 Fracc. Industrial El Trebol
Tepotzotlan, Estado de Mexico C.P. 54600

(Numero) Number **V11C7904**
(Fecha) Date **25/02/2011**

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)
ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PROBADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598	- VALVE INSPECTION AND TESTING
API 599	- METAL PLUG VALVES - FLANGED, THREADED AND WELDING
ANSI B16-10	- FACE TO FACE AND END TO END DIMENSIONS OF VALVES
ANSI B16-34	- VALVES - FLANGED, THREADED AND WELDING ENDS
MSS-SP61	- PRESSURE TESTING OF STEEL VALVES
API 6D	- PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
API 600	- STEEL GATE VALVES, FLANGED AND WELDING ENDS
ANSI B16-11	- FORGED FITTINGS, SOCKET - WELDING AND THREADED
API 602	- COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. (Código) **AC011A08MAA8300000**

Description Descripción **2" Fig. 5202 F UT WCB, API TRIM No.8 830000**

CAST STEEL GATE VALVE 150 CLASS
(VALVULA COMPUERTA DE ACERO FUNDIDO CLASE 150)

VALVE WITH LOW EMISSION CONTROL (50 PPM'S MAX.) (VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS (50 PPM'S MAX.))

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO) 1	SIDE (LADO) 2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N A	N A
PNEUMATIC (PSI) (NEUMATICA)			80	80

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	TENS KPSI CVN@	YIELD KPSI 1ST	ELG % 2ND	RED % 3RD	BHN AVG
BODY CUERPO	WH16830	ASTM A-216/WCB	0.180	0.800	0.028	0.011	0.463	0.031	0.094	0.008	0.035	0.003		73.95	43.79	33	47	158
			Normalized to (Normalizado a) 930				Temper to (Temple a) 650			Cooled in air. (Enfriado en aire.)								
BONNET BONETE	WH25478	ASTM A-216/WCB	0.195	0.944	0.015	0.014	0.405	0.005	0.031	0.005	0.005	0.001		73.95	42.63	25	46	168
			Normalized to (Normalizado a) 930				Temper to (Temple a) 650			Enfriado en aire. (Cooled in air.)								
WEDGE DISCO	D3280	ASTM A-217/CA15	0.090	0.970	0.012	0.010	0.810	0.270	12.720	0.027	0.028	0.001		101.07	68.88	26	46	271
			Normalizado a (Normalizated to) 970				Temple a (Temper to) 630			Enfriado en aire. (Cooled in air.)								

CHEMICAL COMPOSITION (%) — COMPOSICIÓN QUIMICA (%)

MECHANICAL TESTS (PROP. MECANICAS)

FAC10-21 REV "3"

CERTIFICADO POR:
ASEGURAMIENTO DE CALIDAD

CERTIFIED BY :
QUALITY ASSURANCE

Jessica García