

## QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)  
ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PROBADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

- |             |   |             |   |
|-------------|---|-------------|---|
| API 598     | - VALVE INSPECTION AND TESTING                      | API 6D      | - PIPELINE VALVES - GATE, PLUG, BALL AND CHECK                                    |
| API 599     | - METAL PLUG VALVES - FLANGED, THREADED AND WELDING | API 600     | - STEEL GATE VALVES, FLANGED AND WELDING ENDS                                     |
| ANSI B16-10 | - FACE TO FACE AND END TO END DIMENSIONS OF VALVES  | ANSI B16-11 | - FORGED FITTINGS, SOCKET - WELDING AND THREADED                                  |
| ANSI B16-34 | - VALVES - FLANGED, THREADED AND WELDING ENDS       | API 602     | - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS |
| MSS-SP61    | - PRESSURE TESTING OF STEEL VALVES                  |             |   |

Part No. **AC031A08MAB83000AF**  
(Código) **3" Fig. 5202 F UT WCB, API TRIM No.8 83000A**  
Description **CAST STEEL GATE VALVE 150 CLASS**  
Descripción **(VALVULA COMPUERTA DE ACERO FUNDIDO CLASE 150)**

(VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS (50 PPM'S MAX.)

| PRESSURE TEST<br>(PRUEBAS DE PRESION) | SHELL<br>(CASCO) | BACK<br>(SEAT) | SIDE (LADO) |     |
|---------------------------------------|------------------|----------------|-------------|-----|
|                                       |                  |                | 1           | 2   |
| HYDROSTATIC (PSI)<br>(HIDROSTATICA)   | 450              | 450            | N A         | N A |
| PNEUMATIC (PSI)<br>(NEUMATICA)        |                  |                | 80          | 80  |

**MECHANICAL TESTS (PROP. MECANICAS)**

**CHEMICAL COMPOSITION (%)**


COMPOSICIÓN QUIMICA (%)

| ITEM<br>(PARTE)  | HEAT No.<br>(COLADA) | MATERIAL<br>(ASTM) | CHEMICAL COMPOSITION (%)          |       |       |       |                             |       |       |                                 |       |       | TENS  | YIELD        | ELG         | RED      | BHN      |     |
|------------------|----------------------|--------------------|-----------------------------------|-------|-------|-------|-----------------------------|-------|-------|---------------------------------|-------|-------|-------|--------------|-------------|----------|----------|-----|
|                  |                      |                    | C                                 | Mn    | P     | S     | Si                          | Ni    | Cr    | Mo                              | Cu    | V     | Cb    | KPSI<br>CVN@ | KPSI<br>1ST | %<br>2ND | %<br>3RD | AVG |
| BODY<br>CUERPO   | N1728                | ASTM A-216/WCB     | 0.219                             | 0.715 | 0.020 | 0.021 | 0.410                       | 0.030 | 0.120 | 0.015                           | 0.030 | 0.020 |       | 74.68        | 44.23       | 27       | 43       | 168 |
| BONNET<br>BONETE | N1686                | ASTM A-216/WCB     | Normalized (Normalizado a) 930 °C |       |       |       | Temper to (Temple a) 650 °C |       |       | Air Cooled. (Enfriado en aire.) |       |       | 72.50 | 44.95        | 26          | 40       | 166      |     |
| WEDGE<br>DISCO   | 347                  | ASTM A-216/WCB     | 0.190                             | 0.730 | 0.021 | 0.021 | 0.420                       | 0.020 | 0.050 | 0.020                           | 0.140 | 0.000 |       | 72.50        | 42.05       | 29       | 56       | 141 |
|                  |                      |                    | Normalized (Normalizado a) 930 °C |       |       |       | Temper to (Temple a) 650 °C |       |       | Air Cooled. (Enfriado en aire.) |       |       |       |              |             |          |          |     |
|                  |                      |                    | 0.230                             | 0.910 | 0.038 | 0.022 | 0.460                       | 0.019 | 0.026 | 0.001                           | 0.024 | 0.000 |       |              |             |          |          |     |
|                  |                      |                    |                                   |       |       |       |                             |       |       | Air Cooled. (Enfriado en aire.) |       |       |       |              |             |          |          |     |

FAC10-21 REV "3"

CERTIFICADO POR:  
ASEGURAMIENTO DE CALIDAD

CERTIFIED BY:  
QUALITY ASSURANCE

  
Jessica Garcia