

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598	- VALVE INSPECTION AND TESTING	API 6D	- PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
API 599	- METAL PLUG VALVES - FLANGED, THREADED AND WELDING	API 600	- STEEL GATE VALVES, FLANGED AND WELDING ENDS
ANSI B16-10	- FACE TO FACE AND END TO END DIMENSIONS OF VALVES	ANSI B16-11	- FORGED FITTINGS, SOCKET - WELDING AND THREADED
ANSI B16-34	- VALVES - FLANGED, THREADED AND WELDING ENDS	API 602	- COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS
MSS-SP61	- PRESSURE TESTING OF STEEL VALVES		

Part No. **AC061A08MAB83000AF**
(Código)
Description **6" Fig. 5202 F UT WCB, API TRIM No.8 83000A**
Descripción **CAST STEEL GATE VALVE 150 CLASS**
(VALVULA COMPUERTA DE ACERO FUNDIDO CLASE 150)

(VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS (50 PPM'S MAX.)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N A	N A
PNEUMATIC (PSI) (NEUMATICA)			80	80

MECHANICAL TESTS (PROP. MECANICAS)

CHEMICAL COMPOSITION (%)

COMPOSICIÓN QUIMICA (%)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	CHEMICAL COMPOSITION (%)										TENS KPSI CVN@	YIELD KPSI 1ST	ELG % 2ND	RED % 3RD	BHN AVG
			C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V					
BODY CUERPO	Z0193	ASTM A-216/WCB	0.233	0.888	0.029	0.032	0.451	0.018	0.019	0.014	0.014	0.013	71.49	37.99	25	39	158
BONNET BONETE	Z0138	ASTM A-216/WCB	Normalized to (Normalizado a) 930 °C				Temper to (Temple a) 650 °C		Cooled in air. (Enfriado en aire.)			71.63	37.70	24	39	162	
WEDGE DISCO	350	ASTM A-216/WCB	0.230	0.857	0.016	0.012	0.524	0.018	0.011	0.012	0.014	0.012	73.95	45.53	31	52	147
			Normalized to (Normalizado a) 930 °C				Temper to (Temple a) 650 °C		Cooled in air. (Enfriado en aire.)								

CERTIFICADO POR:
ASEGURAMIENTO DE CALIDAD

CERTIFIED BY:
QUALITY ASSURANCE


Jessica Garcia