

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

- | | |
|--|---|
| API 598 - VALVE INSPECTION AND TESTING
API 599 - METAL PLUG VALVES- FLANGED, THREADED AND WELDING
ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES
ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS
MSS-SP61 - PRESSURE TESTING OF STEEL VALVES | API 6D - PIPELINE VALVES- GATE, PLUG, BALL AND CHECK
API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS
ANSI B16-11 - FORGED FITTINGS, SOCKET- WELDING AND THREADED
API 602 - COMPACT STEEL GATE VALVES- FLANGED, THREADED, WELDING AND EXTENDED- BODY ENDS |
|--|---|

Part No. AC041A08MAB830000F
 (Código) **4" Fig. 5202 F UT WCB, API TRIM No.8 830000**
Description
 Descripción **CAST STEEL GATE VALVE 150 CLASS**
(VALVULA COMPUERTA DE ACERO FUNDIDO CLASE 150)

VALVE WITH LOW EMISSION CONTROL (50 PPM'S MAX.) (VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS (50 PPM'S MAX.)

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N A	N A
PNEUMATIC (PSI) (NEUMATICA)			80	80

MECHANICAL TESTS (PROP. MECANICAS)

CHEMICAL COMPOSITION (%)			COMPOSICIÓN QUIMICA (%)										MECHANICAL TESTS (PROP. MECANICAS)					
ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	TENS KPSI CVN@	YIELD KPSI 1ST	ELG % 2ND	RED % 3RD	BHN AVG
BODY CUERPO	N1810	ASTM A-216/WCB	0.219	0.715	0.020	0.021	0.410	0.030	0.120	0.150	0.030	0.020		74.68	43.50	27	43	160
Normalized (Normalizado a) 930 °C			Temper to (Temple a) 650 °C										Air Cooled. (Enfriado en aire.)					
BONNET BONETE	N1779	ASTM A-216/WCB	0.216	0.712	0.020	0.021	0.405	0.020	0.200	0.160	0.022	0.011		72.50	44.23	25	43	162
Normalized (Normalizado a) 930 °C			Temper to (Temple a) 650 °C										Air Cooled. (Enfriado en aire.)					
WEDGE DISCO	336	ASTM A-216/WCB	0.250	0.810	0.021	0.018	0.467	0.001	0.080	0.013	0.020	0.011		76.13	45.68	28	39	152
Normalized (Normalizado a) 930 °C			Temper to (Temple a) 650 °C										Air Cooled. (Enfriado en aire.)					

 CERTIFICADO POR:
 ASEGURAMIENTO DE CALIDAD

 CERTIFIED BY:
 QUALITY ASSURANCE



Jessica Garcia