

# QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

## ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PROBADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598	- VALVE INSPECTION AND TESTING	API 6D	- PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
API 599	- METAL PLUG VALVES - FLANGED, THREADED AND WELDING	API 600	- STEEL GATE VALVES, FLANGED AND WELDING ENDS
ANSI B16-10	- FACE TO FACE AND END TO END DIMENSIONS OF VALVES	ANSI B16-11	- FORGED FITTINGS, SOCKET - WELDING AND THREADED
ANSI B16-34	- VALVES - FLANGED, THREADED AND WELDING ENDS	API 602	- COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS
MSS-SP61	- PRESSURE TESTING OF STEEL VALVES		

**Part No. AC081A08MAB830000Z**

(Código)

**Description**

Descripción

**8" Fig. 5202 F UT WCB, API TRIM No.8 830000**
**CAST STEEL GATE VALVE 150 CLASS**
**(VALVULA COMPUERTA DE ACERO FUNDIDO CLASE 150)**
**VALVE WITH LOW EMISSION CONTROL (50 PPM'S MAX.) (VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS (50 PPM'S MAX.))**

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	NA	NA
PNEUMATIC (PSI) (NEUMATICA)			80	80

**MECHANICAL TESTS (PROP. MECANICAS)**
**CHEMICAL COMPOSITION (%)**
**COMPOSICIÓN QUIMICA (%)**
**TENS YIELD ELG RED BHN**

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	KPSI CVN@	KPSI 1ST	% 2ND	% 3RD	AVG
BODY	K0953	ASTM A-216/WCB	0.220	0.780	0.025	0.031	0.450	0.034	0.028	0.055	0.038	0.010		84.10	40.46	29	42	151
CUERPO			Normalized to (Normalizado a) 930 °C			Temper to (Temple a) 650 °C			Cooled in air. (Enfriado en aire.)									
BONNET	K0811	ASTM A-216/WCB	0.210	0.830	0.026	0.000	0.440	0.016	0.025	0.035	0.068	0.000		77.58	47.85	30	44	151
BONETE			Normalized to (Normalizado a) 930 °C			Temper to (Temple a) 650 °C			Cooled in air. (Enfriado en aire.)									
WEDGE	N3929	ASTM A-216/WCB	0.220	0.760	0.021	0.031	0.380	0.045	0.046	0.009	0.030	0.003		73.23	36.83	24	40	160
DISCO			Normalized to (Normalizado a) 930 °C			Temper to (Temple a) 650 °C			Cooled in air. (Enfriado en aire.)									

 CERTIFICADO POR:  
 ASEGURAMIENTO DE CALIDAD

 CERTIFIED BY:  
 QUALITY ASSURANCE

  
**Jessica Garcia**