



Industrial de Valvulas, S.A. de C.V.
 Av. de La Industria Lote 16 Fracc. Industrial El Trebol
 Tepotzotlan, Estado de Mexico C.P. 54600
 Teléfono: (52 55) 5899 1700 Fax: (52 55) 5876 0156
 E-Mail: Info@walworth.com.mx Web: www.walworthvalves.com

(Numero) Number **V122C6285**
 (Fecha) Date **06/09/2013**

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PROBADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

- | | |
|--|---|
| API 598 - VALVE INSPECTION AND TESTING | API 6D - PIPELINE VALVES - GATE, PLUG, BALL AND CHECK |
| API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING | API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS |
| ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES | ANSI B16-11 - FORGED FITTINGS, SOCKET - WELDING AND THREADED |
| ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS | API 602 - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS |
| MSS-SP61 - PRESSURE TESTING OF STEEL VALVES | |

Part No. AC041A08MAB830000M
 (Código)
Description 4" Fig. 5202 F UT WCB, API TRIM No.8 830000
 Descripción CAST STEEL GATE VALVE 150 CLASS
 (VALVULA COMPUERTA DE ACERO FUNDIDO CLASE 150)
 VALVE WITH LOW EMISSION CONTROL (50 PPM'S MAX.) (VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS (50 PPM'S MAX.))

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	N A	N A
PNEUMATIC (PSI) (NEUMATICA)			80	80

MECHANICAL TEST (PROP. MECANICAS)

CHEMICAL COMPOSITION (%) COMPOSICIÓN QUIMICA (%)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	CHEMICAL COMPOSITION (%)											TENS	YIELD	ELG	RED	BHN		
			C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	KPSI CVN@	KPSI 1ST	% 2ND	% 3RD	AVG		
BODY CUERPO	HC0950	ASTM A-216/WCB	0.200	0.840	0.020	0.013	0.380	0.015	0.043	0.023	0.012	0.001								
			Normalized (Normalizado a) 930 °C																	
			Temper to (Temple a) 650 °C																	
			Air Cooled. (Enfriado en aire.)											74.68	46.40	37	55	159		
BONNET BONETE	HC2040	ASTM A-216/WCB	0.190	0.850	0.017	0.009	0.410	0.012	0.059	0.021	0.009	0.003								
			Normalized (Normalizado a) 930 °C																	
			Temper to (Temple a) 650 °C																	
			Air Cooled. (Enfriado en aire.)											76.13	44.95	28	48	157		
WEDGE DISCO	HC2041	ASTM A-216/WCB	0.210	0.840	0.014	0.008	0.370	0.017	0.053	0.023	0.009	0.003								
			Normalized (Normalizado a) 930 °C																	
			Temper to (Temple a) 650 °C																	
			Air Cooled. (Enfriado en aire.)											76.85	45.68	26	47	158		

FAC10-21 REV "3"

CERTIFICADO POR:
ASEGURAMIENTO DE

CERTIFIED BY:
QUALITY ASSURANCE

Yolanda Ponciano