



WALWORTH

Since 1842

Industrial de Valvulas, S.A. de C.V.

Av. de La Industria Lote 16 Fracc. Industrial El Trebol

Tepotzotlan, Estado de Mexico C.P. 54600

Teléfono: (52 55) 5899 1700 Fax: (52 55) 5876 0156

E-Mail: Info@walworth.com.mx Web: www.walworthvalves.com

(Numero) Number

V128G1428

(Fecha) Date

30/05/2014

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

- API 598 - VALVE INSPECTION AND TESTING
- API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING
- ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES
- ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS
- MSS-SP61 - PRESSURE TESTING OF STEEL VALVES
- API 594 - CHECK VALVES FLANGED, LUG, WAFER AND BUTT WELDING

- API 6D - PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
- API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS
- ANSI B16-11 - FORGED FITTINGS, SOCKET - WELDING AND THREADED
- API 602 - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. AG032A08MAB830000G
 (Código)
Description 3" Fig. 5281 F UT WCB, API TRIM No.8 830000
 Descripción CAST STEEL GLOBE VALVE 300 CLASS
 (VALVULA GLOBO DE ACERO FUNDIDO CLASE 300)

VALVE WITH LOW EMISSION CONTROL (50 PPM'S MAX.) (VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS (50 PPM'S MAX.))

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	1125	1125	815	N A
PNEUMATIC (PSI) (NEUMATICA)			80	N A

MECHANICAL TEST (PROP. MECANICAS)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	CHEMICAL COMPOSITION (%)										TENS KPSI CVN@	YIELD KPSI 1ST	ELG % 2ND	RED % 3RD	BHN AVG
			C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V					
BODY CUERPO	H3352	ASTM A-216/WCB	0.213	0.838	0.028	0.023	0.426	0.043	0.072	0.010	0.050	0.001	73.81	44.37	33	48	159
Normalized (Normalizado a) 910 °C			Temper to (Temple a) 650 °C										Air Cooled. (Enfriado en aire.)				
BONNET BONETE	H3338	ASTM A-216/WCB	0.241	0.863	0.026	0.022	0.386	0.042	0.036	0.016	0.036	0.001	71.63	42.20	28	60	165
Normalized (Normalizado a) 910 °C			Temper to (Temple a) 650 °C										Air Cooled. (Enfriado en aire.)				
WEDGE DISCO	H3352	ASTM A-216/WCB	0.213	0.838	0.028	0.023	0.426	0.043	0.072	0.010	0.050	0.001	73.81	44.37	33	48	159
Normalized (Normalizado a) 910 °C			Temper to (Temple a) 650 °C										Air Cooled. (Enfriado en aire.)				

FAC10-21 REV *3*

CERTIFICADO POR:
ASEGURAMIENTO DE

CERTIFIED BY :
QUALITY ASSURANCE

Yolanda Ponciano