

## QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

### ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PRABADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

- |   |   |
|---|---|
| API 598 - VALVE INSPECTION AND TESTING<br>API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING<br>ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES<br>ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS<br>MSS-SP61 - PRESSURE TESTING OF STEEL VALVES | API 6D - PIPELINE VALVES- GATE, PLUG, BALL AND CHECK<br>API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS<br>ANSI B16-11 - FORGED FITTINGS, SOCKET- WELDING AND THREADED<br>API 602 - COMPACT STEEL GATE VALVES- FLANGED, THREADED, WELDING AND EXTENDED- BODY ENDS |
|---|---|

**Part No. AC031A08MAB830000F**  
 (Código) **3" Fig. 5202 F UT WCB, API TRIM No.8 830000**  
**Description**  
 Descripción **CAST STEEL GATE VALVE 150 CLASS**  
**(VALVULA COMPUERTA DE ACERO FUNDIDO CLASE 150)**

VALVE WITH LOW EMISSION CONTROL (50 PPM'S MAX.) (VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS (50 PPM'S MAX.))

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
<b>HYDROSTATIC (PSI)</b> (HIDROSTATICA)	450	450	N A	N A
<b>PNEUMATIC (PSI)</b> (NEUMATICA)			80	80

#### MECHANICAL TESTS (PROP. MECANICAS)

CHEMICAL COMPOSITION (%)			COMPOSICIÓN QUIMICA (%)										MECHANICAL TESTS (PROP. MECANICAS)					
ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	TENS	YIELD	ELG	RED	BHN
														KPSI CVN@	KPSI 1ST	% 2ND	% 3RD	AVG
BODY	N1798	ASTM A-216/WCB	0.190	0.700	0.019	0.027	0.350	0.038	0.039	0.006	0.026	0.001		71.05	36.39	22	35	155
CUERPO			Normalized (Normalizado a) 920 °C															
BONNET	N1723	ASTM A-216/WCB	0.218	0.710	0.020	0.021	0.400	0.070	0.160	0.110	0.020	0.015		73.95	45.68	25	40	155
BONETE			Normalized (Normalizado a) 930 °C															
WEDGE	356	ASTM A-216/WCB	0.210	0.870	0.033	0.023	0.430	0.052	0.043	0.015	0.066	0.000		72.50	42.78	29	56	141
DISCO			Temper to (Temple a) 650 °C															
			Air Cooled. (Enfriado en aire.)															

 CERTIFICADO POR:  
 ASEGURAMIENTO DE CALIDAD

 CERTIFIED BY :  
 QUALITY ASSURANCE

  
 Jessica Garcia