



**WALWORTH**  
Since 1842

Industrial de Valvulas, S.A. de C.V.  
Industria Lote 16 Fracc. Industrial El Trebol de Tepotzotlan  
Tepotzotlan, Estado de Mexico C.P. 54610  
Teléfono: (52 55) 5899 1700 Fax: (52 55) 5876 0156  
E-Mail: info@walworth.com.mx Web: www.walworthvalves.com

(Numero) Number

V12LC11765

(Fecha) Date

16/07/2015

## QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

### ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PROBADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598 - VALVE INSPECTION AND TESTING  
API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING  
ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES  
ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS  
MSS-SP61 - PRESSURE TESTING OF STEEL VALVES  
API 594 - CHECK VALVES FLANGED, LUG, WAFER AND BUTT WELDING

API 6D - PIPELINE VALVES - GATE, PLUG, BALL AND CHECK  
API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS  
ANSI B16-11 - FORGED FITTINGS, SOCKET - WELDING AND THREADED  
API 602 - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

**Part No.** AC011A08MAB830000H  
(Código)  
**Description** 2" Fig. 5202 F UT WCB, API TRIM No.8 830000  
Descripción CAST STEEL GATE VALVE 150 CLASS  
(VALVULA COMPUERTA DE ACERO FUNDIDO CLASE 150)

VALVE WITH LOW EMISSION CONTROL (50 PPM'S MAX.) (VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS (50 PPM'S MAX.) )

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO)	
			1	2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	450	NA	NA
PNEUMATIC (PSI) (NEUMATICA)			80	80

### MECHANICAL TEST (PROP. MECANICAS)

### CHEMICAL COMPOSITION (%) COMPOSICIÓN QUIMICA (%)

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	CHEMICAL COMPOSITION (%)											TENS	YIELD	ELG	RED	BHN		
			C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	KPSI CVN@	KPSI 1ST	% 2ND	% 3RD	AVG		
BODY CUERPO	7046	ASTMA-216 GR WCB Normalized (Normalizado a) 930 °C	0.170	0.750	0.030	0.027	0.340	0.026	0.027	0.008	0.026	0.002				76.27	41.18	29	40	165
BONNET BONETE	7113	ASTMA-216 GR WCB Normalized (Normalizado a) 930 °C	0.190	0.650	0.030	0.027	0.370	0.029	0.025	0.008	0.030	0.002				74.82	40.60	28	40	160
WEDGE DISCO	0007	ASTMA-216 GR WCB Normalized (Normalizado a) 930 °C	0.210	0.680	0.025	0.021	0.430	0.051	0.054	0.004	0.024	0.003				76.42	45.97	32	43	152

FAC10-21 REV 13\*

CERTIFICADO POR:  
ASEGURAMIENTO DE

CERTIFIED BY:  
QUALITY ASSURANCE

Yolanda Ponciano