WALWORTH® Since 1842
Industrial de Valvulas, S.A. de C.V.
Industria Lote 16 Fracc. Industrial El Trebol de Tepotzotlan
Tepotzotlan, Estado de Mexico C.P. 54610
Teléfono: (52 55) 5899 1700 Fax: (52 55) 5876 0156
E-Mail: Info@walworth.com.mx Web: www.walworthvalves.com

(Numero) Number V132R1166
(Fecha) Date 26/08/2015

QUALITY ASSURANCE CERTIFICATE OF COMPLIANCE

(ACCORDING TO EN10204 TYPE 3.1)

ASEGURAMIENTO DE CALIDAD CERTIFICADO DE CUMPLIMIENTO

WE CERTIFY THAT THE PRODUCT LISTED BELOW WAS DESIGNED, MANUFACTURED AND TESTED ACCORDING TO OUR QUALITY SYSTEM AND REQUIREMENTS GIVEN IN ONE OR MORE OF THE FOLLOWING STANDARDS LAST EDITION:

(CERTIFICAMOS QUE EL PRODUCTO LISTADO ABAJO FUE DISEÑADO, FABRICADO Y PROBADO DE ACUERDO CON NUESTRO SISTEMA DE CALIDAD Y CON REQUISITOS ESTABLECIDOS EN UNO O MAS DE LOS SIGUIENTES ESTANDARES ULTIMA EDICIÓN.)

API 598 - VALVE INSPECTION AND TESTING
API 599 - METAL PLUG VALVES - FLANGED, THREADED AND WELDING
ANSI B16-10 - FACE TO FACE AND END TO END DIMENSIONS OF VALVES
ANSI B16-34 - VALVES - FLANGED, THREADED AND WELDING ENDS
MSS-SP61 - PRESSURE TESTING OF STEEL VALVES
API 594 - CHECK VALVES FLANGED, LUG, WAFER AND BUTT WELDING
API 6D - PIPELINE VALVES - GATE, PLUG, BALL AND CHECK
API 600 - STEEL GATE VALVES, FLANGED AND WELDING ENDS
ANSI B16-11 - FORGED FITTINGS, SOCKET - WELDING AND THREADED
API 602 - COMPACT STEEL GATE VALVES - FLANGED, THREADED, WELDING AND EXTENDED - BODY ENDS

Part No. (Código) **AR061A08MAB830000Z**

Description (Descripción) **6" Fig. 5341 F UT WCB, API TRIM No.8 830000**

CAST STEEL SWING CHECK VALVE 150 CLASS
(VALVULA RETENCIÓN TIPO COLUMPIO DE ACERO FUNDIDO CLASE 150)

VALVE WITH LOW EMISSION CONTROL (50 PPM'S MAX.) (VALVULA SUMINISTRADA CON CONTROL DE BAJAS EMISIONES FUGITIVAS (50 PPM'S MAX.))

PRESSURE TEST (PRUEBAS DE PRESION)	SHELL (CASCO)	BACK (SEAT)	SIDE (LADO) 1	SIDE (LADO) 2
HYDROSTATIC (PSI) (HIDROSTATICA)	450	NA	315	NA
PNEUMATIC (PSI) (NEUMATICA)			NA	NA

ITEM (PARTE)	HEAT No. (COLADA)	MATERIAL (ASTM)	C	Mn	P	S	Si	Ni	Cr	Mo	Cu	V	Cb	TENS KPSI CVN@	YIELD KPSI 1ST	ELG % 2ND	RED % 3RD	BHN AVG
			CHEMICAL COMPOSITION (%) / COMPOSICIÓN QUIMICA (%)											MECHANICAL TEST (PROP. MECANICAS)				
BODY CUERPO	K1031	ASTM A-216 GR WCB	0.191	0.758	0.024	0.013	0.442	0.050	0.071	0.092	0.039	0.016		72.79	41.91	28	40	155
		Normalized (Normalizado a) 930 °C				Temper to (Temple a) 650 °C				Air Cooled. (Enfriado en aire.)								
COVER TAPA	K0069	ASTM A-216 GR WCB	0.190	0.810	0.008	0.020	0.420	0.024	0.022	0.023	0.027	0.003		75.84	42.78	28	37	160
		Normalized (Normalizado a) 930 °C				Temper to (Temple a) 650 °C				Air Cooled. (Enfriado en aire.)								
WEDGE DISCO	1002131	ASTM A-105N	0.220	0.920	0.013	0.004	0.210	0.010	0.060	0.004	0.070	0.005		74.97	46.69	30	69	150
		Normalized (Normalizado a) 930 °C				650 °C				Air Cooled (Enfriado en aire)								

FAC10-21 REV."3"

CERTIFICADO POR: ASEGURAMIENTO DE

CERTIFIED BY : QUALITY ASSURANCE

Yolanda Ponciano