



**WALWORTH**  
Since 1842

Industrial de Válvulas, S.A. de C.V.

Industria Ite 16 S/N Fracc. Industrial el Trébol de  
Tepozotlán, Estado de México, México C.P. 54610

**CERTIFICATE OF MATERIALS & TEST REPORT (CMTR)**  
(CERTIFICADO DE CALIDAD DE MATERIALES Y REPORTE DE PRUEBAS CMTR)  
ACCORDING TO EN 10204 TYPE 3.1

No. código interno (Product Code Nr.): **AC020BA08MA2A1BG**

No. Serie (Serial Number): **V138C12010**

Fecha (Date): **May 25, 2016**

No. De Tag (Tag Number):

Clientes (Customer): **PLESA ANAHUAC Y CIAS, S.A DE C.V.**

No Pedido del Cliente (Customer PO Nr.): **22817**

Partida (Customer Item): **12** Pedido Interno No (Walworth Sales Nr.): **D000060182**

Partida (Item): **33**

Linea de producto (Product line):	<b>CAST STEEL</b>	Extremos (Ends):	<b>RAISED FACE (RF TYPE "A")</b>	Operación (Operation):	<b>HANDWHEEL</b>
Tipo de válvula (Type of valve):	<b>GATE OS &amp; Y</b>	Cuerpo (Shell):	<b>WCB</b>	Otros (Other requirements):	
Diámetro (Nominal diameter):	<b>2</b>	Interiores (Trim):	<b>#08 (UT)</b>		
Presión clase (Pressure class):	<b>150</b>	Figura No (Figure Nr.):	<b>FIG 5202</b>		

**COMPOSICION QUIMICA EN % (CHEMICAL COMPOSITION %)**


Parte (Component)	Material (Material)	Colada (Heat)	% C	% Mn	% P	% S	% Si	% Ni	% Cr	% Mo	% Cu	% V	%	%	%	%	%	%	%
BONETE (BONNET)	ASTM_A_216_GR_WCB	H9706	0.207	0.698	0.022	0.028	0.356	0.035	0.076	0.014	0.031	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000
CUERPO (BODY)	ASTM_A_216_GR_WCB	K4127	0.174	0.843	0.018	0.010	0.389	0.035	0.054	0.008	0.024	0.008	0.000	0.000	0.000	0.000	0.000	0.000	0.000
DISCO 1 (DISC 1)	ASTM_A_216_GR_WCB	4403	0.199	0.694	0.026	0.020	0.369	0.044	0.055	0.011	0.034	0.001	0.000	0.000	0.000	0.000	0.000	0.000	0.000

**PROPIEDADES MECANICAS (MECHANICAL TESTING)**

Parte (Component)	Colada (Heat)	Condición de TT Normalizado & revenido Heat Treatment condition (Normalized & tempered)	Cedencia (Yield strength) (Kpsi)	Tensión (Tensile strength) (Kpsi)	Alar. En 2" (Elong. In 2") (% min)	Reduccion de area (Reduction of area) (% min)	Dureza (Hardness) (Bhn)		Prueba Impacto (Impact Test) (Joules)				
							1st	2nd	1st	2nd	3rd	AVG	
BONETE (BONNET)	H9706	(910-940) °C, NORMALIZADO ( RECOCIDO ) 650 °C ENFRIAMIENTO CON AIRE (910-940) °C, NORMALIZE ( ANNEAL ) 650 °C AIR COOL	44.5150	81.2000	31	64	150	0	0	0	0	0	0
CUERPO (BODY)	K4127	(910-940) °C, NORMALIZADO ( RECOCIDO ) 650 °C ENFRIAMIENTO CON AIRE (910-940) °C, NORMALIZE ( ANNEAL ) 650 °C AIR COOL	53.6500	79.7500	32	52	156	0	0	0	0	0	0
DISCO 1 (DISC 1)	4403	(910-940) °C, NORMALIZADO ( RECOCIDO ) 650 °C ENFRIAMIENTO CON AIRE (910-940) °C, NORMALIZE ( ANNEAL ) 650 °C AIR COOL	46.2550	81.0550	34	43	151	0	0	0	0	0	0

**PRUEBAS DE PRESIÓN DE ACUERDO CON API 598 (PRESSURE TEST IN ACCORDANCE WITH API 598)**

TIPO DE PRUEBA (Type of test)	PRESION (Pressure) (Psi)	TIEMPO (Duration) (min)	RESULTADO (Result)	TIPO DE PRUEBA (Type of test)	RESULTADO (Result)
HIDROSTATICA DE CASCO (HYDROSTATIC SHELL)	450	1 min	ACEPTADO (ACCEPTED)		
HIDROSTATICA DE CASQUILLO (HYDROSTATIC BACK SEAT)	450	1 min	ACEPTADO (ACCEPTED)		
PRUEBA NEUMATICA SELLO 1 (LOW PRESSURE CLOSURE SIDE 1)	80	1 min	ACEPTADO (ACCEPTED)		
PRUEBA NEUMATICA SELLO 2 (LOW PRESSURE CLOSURE SIDE 2)	80	1 min	ACEPTADO (ACCEPTED)		



Certificamos que este producto ha sido diseñado, fabricado y probado de acuerdo con nuestro sistema de administración de calidad y con los requisitos establecidos en una o más de las siguientes normas en su última edición. (We hereby certify this product has been designed, manufactured and tested according to our quality management system and requirements stated in one or more of the following standards on their latest edition).

API 599 METAL PLUG VALVES - FLANGED, THREADED AND WELDING  
API 591 PROCESS VALVE QUALIFICATION PROCEDURE  
API 623 STEEL GLOBE VALVES-FLANGED AND BUTT-WELDING ENDS, BOLTED BONNETS  
API 624 TYPE TESTING OF RISING STEM VALVES EQUIPPED WITH GRAPHITE PACKING FOR FUGITIVE EMISSIONS  
ANSI B16-10 FACE TO FACE AND END TO END DIMENSIONS OF VALVES  
ANSI B16-11 FORGED FITTINGS, SOCKET, WELDING AND THREADED  
ANSI/NACE MR0175/ISO 15156-1 MATERIALS FOR USE IN H<sub>2</sub>S-CONTAINING ENVIRONMENTS IN OIL AND GAS PRODUCTION  
NACE MR0103 MATERIAL RESISTANT TO SULFIDE STRESS CRACKING IN CORROSIVE PETROLEUM ENVIRONMENT  
MSS-5991 PRESSURE TESTING OF STEEL VALVES

Quality Assurance Department  
Yolanda Ponciano Montoya

FAC-24 Rev. Original.