

CERTIFICATE OF MATERIALS & TEST REPORT (CMTR)
 (CERTIFICADO DE CALIDAD DE MATERIALES Y REPORTE DE PRUEBAS CMTR)
 ACCORDING TO EN 10204 TYPE 3.1

 No. código interno (Product Code Nr.): **AC030BA08MA2A1XH**

 No. Serie (Serial Number): **V14LC4507**

 Fecha (Date): **April 27, 2016**

No. De Tag (Tag Number): _____

 Clientes (Customer): **PLESA ANAHUAC Y CIAS, S.A DE C.V.**

 No Pedido del Cliente (Customer PO Nr.): **23147**

 Partida (Customer Item): **4** Pedido Interno No (Walworth Sales Nr.): **D000060183**

 Partida (Item): **23**

Linea de producto (Product line):	CAST STEEL	Extremos (Ends):	RAISED FACE (RF TYPE "A")	Operación (Operation):	HANDWHEEL
Tipo de válvula (Type of valve):	GATE OS & Y	Cuerpo (Shell):	WCB	Otros (Other requirements):	
Diámetro (Nominal diameter):	3	Interiores (Trim):	#08 (UT)		
Presión clase (Pressure class):	150	Figura No (Figure Nr.):	FIG 5202		

COMPOSICION QUIMICA EN % (CHEMICAL COMPOSITION %)

Parte (Component)	Material (Material)	Colada (Heat)	% C	% Mn	% P	% S	% Si	% Ni	% Cr	% Mo	% Cu	% V	%	%	%	%	%	%
BONETE (BONNET)	ASTM_A_216_GR_WCB	7116	0.220	0.680	0.017	0.019	0.460	0.024	0.036	0.002	0.016	0.001	0.000	0.000	0.000	0.000	0.000	0.000
CUERPO (BODY)	ASTM_A_216_GR_WCB	6062	0.230	0.770	0.014	0.014	0.460	0.040	0.170	0.060	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000
DISCO 1 (DISC 1)	ASTM_A_216_GR_WCB	7116	0.220	0.680	0.017	0.019	0.460	0.024	0.036	0.002	0.016	0.001	0.000	0.000	0.000	0.000	0.000	0.000

PROPIEDADES MECANICAS (MECHANICAL TESTING)

Parte (Component)	Colada (Heat)	Condición de TT Normalizado & revenido Heat Treatment condition (Normalized & tempered)	Cedencia (Yield strength) (Kpsi)	Tensión (Tensile strength) (Kpsi)	Alar. En 2" (Elong. In 2") (% min)	Reduccion de area (Reduction of area) (% min)	Dureza (Hardness) (Bhn)		Prueba Impacto (Impact Test) (Joules)				
							1st	2nd	1st	2nd	3rd	AVG	
BONETE (BONNET)	7116	(910-940) °C, NORMALIZADO (RECOCIDO) 650 °C ENFRIAMIENTO CON AIRE	46.5450	75.6900	30	42	150	0	0	0	0	0	0
CUERPO (BODY)	6062	(910-940) °C, NORMALIZADO (RECOCIDO) 650 °C ENFRIAMIENTO CON AIRE	43.2100	72.3550	26	44	165	0	0	0	0	0	0
DISCO 1 (DISC 1)	7116	(910-940) °C, NORMALIZADO (RECOCIDO) 650 °C ENFRIAMIENTO CON AIRE	46.5450	75.6900	30	42	150	0	0	0	0	0	0

PRUEBAS DE PRESIÓN DE ACUERDO CON API 598 (PRESSURE TEST IN ACCORDANCE WITH API 598)

TIPO DE PRUEBA (Type of test)	PRESION (Pressure) (Psi)	TIEMPO (Duration) (min)	RESULTADO (Result)	TIPO DE PRUEBA (Type of test)	RESULTADO (Result)
HIDROSTATICA DE CASCO (HYDROSTATIC SHELL)	450	1 min	ACEPTADO (ACCEPTED)		
HIDROSTATICA DE CASQUILLO (HYDROSTATIC BACK SEAT)	450	1 min	ACEPTADO (ACCEPTED)		
PRUEBA NEUMATICA SELLO 1 (LOW PRESSURE CLOSURE SIDE 1)	80	1 min	ACEPTADO (ACCEPTED)		
PRUEBA NEUMATICA SELLO 2 (LOW PRESSURE CLOSURE SIDE 2)	80	1 min	ACEPTADO (ACCEPTED)		

Certificamos que este producto ha sido diseñado, fabricado y probado de acuerdo con nuestro sistema de administración de calidad y con los requisitos establecidos en una o más de las siguientes normas en su última edición. (We hereby certify this product has been designed, manufactured and tested according to our quality management system and requirements stated in one or more of the following standards on their latest edition).

DESIGN IN ACCORDANCE WITH API 601 / CAST STEEL GATE (OS & YOKER)
 API 609 METAL PLUG VALVES - FLANGED, THREADED AND WELDING
 API 591 PROCESS VALVE QUALIFICATION PROCEDURE
 API 623 STEEL GLOBE VALVES - FLANGED AND BUTT WELDING ENDS, BOLTED BONNETS
 API 624 TYPE TESTING OF RISING STEM VALVES EQUIPPED WITH GRAPHITE PACKING FOR FUGITIVE EMISSIONS
 ANSI B16-16 FACE TO FACE AND END TO END DIMENSIONS OF VALVES
 ANSI B16-11 FORGED FITTINGS, SOCKET - WELDING AND THREADED
 ANNUNCIATOR MR0175950 15156-1 MATERIALS FOR USE IN H₂S-CONTAINING ENVIRONMENTS IN OIL AND GAS PRODUCTION
 NACE MR010 MATERIALS RESISTANT TO SULFIDE STRESS CRACKING IN CORROSIIVE PETROLEUM ENVIRONMENT
 MSS-SP61 PRESSURE TESTING OF STEEL VALVES



 Quality Assurance Department
 Jessica Garcia Pérez

FAC-24 Rev. Original.