



Industrial de Válvulas, S.A. de C.V.

Industria Ite 16 S/N Fracc. Industrial el Trébol de Tepozotlán, Estado de México, México C.P. 54610

CERTIFICATE OF MATERIALS & TEST REPORT (CMTR)
 (CERTIFICADO DE CALIDAD DE MATERIALES Y REPORTE DE PRUEBAS CMTR)
 ACCORDING TO EN 10204 TYPE 3.1

No. código interno (Product Code Nr.): **AR060BA08MANA1BG**

No. Serie (Serial Number): **V158R1133**

Fecha (Date): **July 26, 2016**

No. De Tag (Tag Number): _____

Clientes (Customer): _____

No Pedido del Cliente (Customer PO Nr.): _____

Partida (Customer Item): _____ Pedido Interno No (Walworth Sales Nr.): _____

Partida (Item): _____

Linea de producto (Product line):	Cast Steel	Extremos (Ends):	RF Series A	Operación (Operation):	N/A
Tipo de válvula (Type of valve):	Check Type Swing	Cuerpo (Shell):	WCB	Otros (Other requirements):	
Diámetro (Nominal diameter):	6	Interiores (Trim):	#08 (UT)		
Presión clase (Pressure class):	150	Figura No (Figure Nr.):	FIG 5341		

COMPOSICION QUIMICA EN % (CHEMICAL COMPOSITION %)

Parte (Component)	Material (Material)	Colada (Heat)	% C	% Mn	% P	% S	% Si	% Ni	% Cr	% Mo	% Cu	% V	%	%	%	%	%	%
CUERPO (BODY)	ASTM_A_216_GR_WCB	K5788	0.207	0.832	0.031	0.024	0.365	0.031	0.081	0.010	0.043	0.001	0.000	0.000	0.000	0.000	0.000	0.000
DISCO 1 (DISC 1)	ASTM_A_216_GR_WCB	K5688	0.191	0.907	0.021	0.011	0.345	0.038	0.070	0.012	0.038	0.005	0.000	0.000	0.000	0.000	0.000	0.000
TAPA 1 (COVER 1)	ASTM_A_216_GR_WCB	K5787	0.207	0.653	0.028	0.028	0.395	0.037	0.057	0.020	0.034	0.001	0.000	0.000	0.000	0.000	0.000	0.000

PROPIEDADES MECANICAS (MECHANICAL TESTING)

Parte (Component)	Colada (Heat)	Condición de TT Normalizado & revenido Heat Treatment condition (Normalized & tempered)	Cedencia (Yield strength) (Kpsi)	Tensión (Tensile strength) (Kpsi)	Alar. En 2" (Elong. In 2") (% min)	Reduccion de area (Reduction of area) (% min)	Dureza (Hardness) (Bhn)		Prueba Impacto (Impact Test) (Joules)				
							1st	2nd	1st	2nd	3rd	AVG	
CUERPO (BODY)	K5788	(910-940) °C, NORMALIZADO (RECOCIDO) 650 °C ENFRIAMIENTO CON AIRE (910-940) °C, NORMALIZE (ANNEAL) 650 °C AIR COOL	45.0950	89.9000	26	40	169	0	0	0	0	0	0
DISCO 1 (DISC 1)	K5688	(910-940) °C, NORMALIZADO (RECOCIDO) 650 °C ENFRIAMIENTO CON AIRE (910-940) °C, NORMALIZE (ANNEAL) 650 °C AIR COOL	53.6500	79.7500	31	54	154	0	0	0	0	0	0
TAPA 1 (COVER 1)	K5787	(910-940) °C, NORMALIZADO (RECOCIDO) 650 °C ENFRIAMIENTO CON AIRE (910-940) °C, NORMALIZE (ANNEAL) 650 °C AIR COOL	43.0650	82.5050	35	46	161	0	0	0	0	0	0

PRUEBAS DE PRESIÓN DE ACUERDO CON API 6D (PRESSURE TEST IN ACCORDANCE WITH API 6D)

TIPO DE PRUEBA (Type of test)	PRESION (Pressure) (Psi)	TIEMPO (Duration) (min)	RESULTADO (Result)	TIPO DE PRUEBA (Type of test)	RESULTADO (Result)
HIDROSTATICA DE CASCO (HYDROSTATIC SHELL)	450	5 min	ACEPTADO (ACCEPTED)		
PRUEBA HIDROSTATICA SELLO 1 (HIGH PRESSURE CLOSURE SIDE 1)	315	5 min	ACEPTADO (ACCEPTED)		



Certificamos que este producto ha sido diseñado, fabricado y probado de acuerdo con nuestro sistema de administración de calidad y con los requisitos establecidos en una o más de las siguientes normas en su última edición. (We hereby certify this product has been designed, manufactured and tested according to our quality management system and requirements stated in one or more of the following standards on their latest edition).

- API 599 METAL PLUG VALVES - FLANGED, THREADED AND WELDING
- API 591 PROCESS VALVE QUALIFICATION PROCEDURE
- API 523 STEEL GLOBE VALVES—FLANGED AND BUTT-WELDING ENDS, BOLTED BONNETS
- API 624 TYPE TESTING OF RISING STEM VALVES EQUIPPED WITH GRAPHITE PACKING FOR FUGITIVE EMISSIONS
- ANSI B16-10 FACE TO FACE AND END TO END DIMENSIONS OF VALVES
- ANSI B16-11 FORGED FITTINGS, SOCKET - WELDING AND THREADED
- ANSI/MSC MRO17/ISO 15159-1 MATERIALS FOR USE IN H2S-CONTAINING ENVIRONMENTS IN OIL AND GAS PRODUCTION
- NACE MR0103 MATERIAL RESISTANT TO SULFIDE STRESS CRACKING IN CORROSIVE PETROLEUM ENVIRONMENT
- MSS-SP61 PRESSURE TESTING OF STEEL VALVES

Quality Assurance Department
 Yolanda Ponciano Montoya
 FAC-24 Rev. Original.