

**Sales Agent:**  
 ArcelorMittal Int. North America  
 1 South Dearborn, 13th floor  
 CHICAGO IL 60603  
 USA

**ArcelorMittal Belval & Differdange**  
 Service Gestion Qualité  
 66, rue de Luxembourg  
 L-4009 Esch/Alzette



**Plant:**  
 ArcelorMittal Belval & Differdange  
 Site de Differdange  
 L-4503 Differdange

**Certificate Nr X 3013072**

Delivery note number 3013072 from 2 May 2015

Our reference : 1700020456  
 Your reference : 20773  
 24.03.2015  
 Plesa Anahuac Y Cias, S.A. de C.V.

Plesa Anahuac Y Cias, S.A. de C.V.  
 Av. Valle de las Alamedas 66-0  
 54940 COL. S. FRANCISCO CHILPAN, TUL  
 MEXICO

**ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED**

Manufacturer's test certificate acc. to ASTM A 6

Ord.item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars
000001	W 18 X 11 X 119	40' 12.192 mm	2,158 mt	02501	2,158 mt		1

Heat nr	Heat analysis (%)															
	C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	CEV	Sn	Nb+V	
	Min	0,50			0,10											
	Max	0,23	1,60	0,035	0,045	0,40	0,60	0,45	0,35	0,150	0,050	0,150	0,45		0,150	
02501		0,07	1,47	0,021	0,020	0,19	0,010	0,22	0,13	0,10	0,053	0,001	0,040	0,38	0,02	0,054

Heat nr	Tensile test				
	PSI	PS: 200 mm	Ys	UTS El. (%) Y/U	
	Min	50.000	65.000	18,00	
	Max	65.000		0,85	
02501		58.870	75.110	22,29	0,78
02501		57.710	73.660	22,00	0,78

Customer ref :  
 000001 : ANA ANGELE

Klecker Roberto  
 Porteur de signature spéciale

**Sales Agent:**  
 ArcelorMittal Int. North America  
 1 South Dearborn, 13th floor  
 CHICAGO IL 60603  
 USA

**ArcelorMittal Belval & Differdange**  
 Service Gestion Qualité  
 66, rue de Luxembourg  
 L-4009 Esch/Alzette



**Plant:**  
 ArcelorMittal Belval & Differdange  
 Site de Differdange  
 L-4503 Differdange

**Certificate NrX 3012667**

Delivery note number 3012667 from 30 April 2015

Our reference : 1700020456  
 Your reference : 20773  
 24.03.2015  
 Plesa Anahuac Y Cias, S.A. de C.V.

Plesa Anahuac Y Cias, S.A. de C.V.  
 Av. Valle de las Alamedas 66-O  
 54940 COL. S. FRANCISCO CHILPAN, TUL  
 MEXICO

**ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED**

Manufacturer's test certificate acc. to ASTM A 6

Ord.item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars
000001	W 18 X 11 X 119	40' 12.192 mm	15,106 mt	02876	15,106 mt		7



Heat nr	Heat analysis (%)															
	C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	CEV	Sn	Nb+V	
	Min	0,50			0,10											
	Max	0,23	1,60	0,035	0,045	0,40	0,60	0,45	0,35	0,150	0,050	0,150	0,45	0,150	0,150	
02876		0,13	1,43	0,018	0,022	0,20	0,010	0,38	0,20	0,09	0,009	0,005	0,050	0,44	0,02	0,014



Heat nr	Tensile test				
	PSI	PSI	UTS	El. (%)	Y/U
	200 mm				
	Min	50.000	65.000	18,00	
	Max	65.000		0,85	
02876		59.015	83.230	24,06	0,71
02876		56.695	83.810	22,39	0,68

Customer ref :  
 000001 : ANA ANGELE

Klecker Roberto  
 Porteur de signature spéciale



<b>Sales Agent:</b> ArcelorMittal Int. North America 1 South Dearborn, 13th floor CHICAGO IL 60603 USA		<b>ArcelorMittal Belval &amp; Differdange</b>  Service Gestion Qualité 66, rue de Luxembourg L-4009 Esch/Alzette																	
<b>Plant:</b> ArcelorMittal Belval & Differdange Site de Differdange L-4503 Differdange		<b>Certificate NrX 3010851</b> Delivery note number 3010851 from 29 April 2015																	
Our reference : 1700020456 Your reference : 20773 24.03.2015 Plesa Anahuac Y Cias, S.A. de C.V.		Plesa Anahuac Y Cias, S.A. de C.V. Av. Valle de las Alamedas 66-0 54940 COL. S. FRANCISCO CHILPAN, TUL MEXICO																	
<b>ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED</b>																			
<b>Manufacturer's test certificate acc. to ASTM A 6</b>																			
<table border="1"> <thead> <tr> <th>Ord.item</th> <th>Product</th> <th>Length</th> <th>Weight</th> <th>Heat nr</th> <th>Weight</th> <th>Bund.</th> <th>Bars</th> </tr> </thead> <tbody> <tr> <td>000001</td> <td>W 18 X 11 X 119</td> <td>40' 12.192 mm</td> <td>4,316 mt</td> <td>02876</td> <td>4,316 mt</td> <td></td> <td>2</td> </tr> </tbody> </table>				Ord.item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars	000001	W 18 X 11 X 119	40' 12.192 mm	4,316 mt	02876	4,316 mt		2
Ord.item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars												
000001	W 18 X 11 X 119	40' 12.192 mm	4,316 mt	02876	4,316 mt		2												
<b>Heat nr</b>		<b>Heat analysis (%)</b>																	
		C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	CEV	Sn	Nb+V			
<b>Min</b>		0,50		0,10															
<b>Max</b>		0,23	1,60	0,035	0,045	0,40		0,60	0,45	0,35	0,150	0,050	0,150	0,45		0,150			
02876		0,13	1,43	0,018	0,022	0,20	0,010	0,38	0,20	0,09	0,009	0,005	0,050	0,44	0,02	0,014			
<b>Heat nr</b>		<b>Tensile test</b>																	
		PSI		PSI 200 mm															
		Ys	UTS	El. (%)	Y/U														
<b>Min</b>		50.000	65.000	18,00															
<b>Max</b>		65.000		0,85															
02876		59.015	83.230	24,06	0,71														
02876		56.695	83.810	22,39	0,68														
Customer ref : 000001 : ANA ANGELE																			
Klecker Roberto Porteur de signature spéciale 																			

<b>Sales Agent:</b> ArcelorMittal Int. North America 1 South Dearborn, 13th floor CHICAGO IL 60603 USA		<b>ArcelorMittal Belval &amp; Differdange</b>  Service Gestion Qualité 66, rue de Luxembourg L-4009 Esch/Alzette													
<b>Plant:</b> ArcelorMittal Belval & Differdange Site de Differdange L-4503 Differdange		<b>Certificate NrX 3015056</b> Delivery note number 3015056 from 5 May 2015													
Our reference : 1700020456 Your reference : 20773 24.03.2015 Plesa Anahuac Y Cias, S.A. de C.V.		Plesa Anahuac Y Cias, S.A. de C.V. Av. Valle de las Alamedas 66-0 54940 COL. S. FRANCISCO CHILPAN, TUL MEXICO													
<b>ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED</b>															
<b>Manufacturer's test certificate acc. to ASTM A 6</b>															
<b>Ord. Item</b>	<b>Product</b>	<b>Length</b>	<b>Weight</b>	<b>Heat nr</b>	<b>Weight</b>	<b>Bund.</b>	<b>Bars</b>								
000002	W 27 X 10 X 94	40' 12.192 mm	3,414 mt	02771	3,414 mt		2								
<b>Heat nr</b>	<b>Heat analysis (%)</b>														
	C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	CEV	Sn	Nb+V
	<b>Min</b>	0,50			0,10										
	<b>Max</b>	0,23	1,60	0,035	0,045	0,40	0,60	0,45	0,35	0,150	0,050	0,150	0,45		0,150
02771		0,08	1,18	0,023	0,016	0,18	0,010	0,21	0,11	0,13	0,041	0,001	0,030	0,34	0,02 0,042
<b>Heat nr</b>	<b>Tensile test</b>														
	PSI	PSI	200 mm.												
	<b>Ys</b>	<b>UTS</b>	<b>El. (%)</b>	<b>Y/U</b>											
	<b>Min</b>	50.000	65.000	18,00											
	<b>Max</b>	65.000		0,85											
02771		58.435	72.500	28,02	0,81										
02771		57.275	72.355	27,70	0,79										
<b>Customer ref :</b> 000002 : ANA ANGELE															
Klecker Roberto Porteur de signature spéciale 															

**Sales Agent:**  
 ArcelorMittal Int. North America  
 1 South Dearborn, 13th floor  
 CHICAGO IL 60603  
 USA

**ArcelorMittal Belval & Differdange**  
 Service Gestion Qualité  
 66, rue de Luxembourg  
 L-4009 Esch/Alzette



**Plant:**  
 ArcelorMittal Belval & Differdange  
 Site de Differdange  
 L-4503 Differdange

**Certificate Nr X 3010864**  
 Delivery note number 3010864 from 29 April 2015

Our reference : 1700020456  
 Your reference : 20773  
 24.03.2015  
 Plesa Anahuac Y Cias, S.A. de C.V.

Plesa Anahuac Y Cias, S.A. de C.V.  
 Av. Valle de las Alamedas 66-O  
 54940 COL. S. FRANCISCO CHILPAN, TUL  
 MEXICO

ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED

Manufacturer's test certificate acc. to ASTM A 6


Ord. Item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars
000002	W 27 X 10 X 94	40' 12.192 mm	6.828 mt	02771	6.828 mt		4

Heat nr	Heat analysis (%)															
	C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	CEV	Sn	Nb+V	
	Min	0,50			0,10											
	Max	0,23	1,60	0,035	0,045	0,40	0,60	0,45	0,35	0,150	0,050	0,150	0,45	0,150		
02771		0,08	1,18	0,023	0,016	0,18	0,010	0,21	0,11	0,13	0,041	0,001	0,030	0,34	0,02	0,042

Heat nr	Tensile test			
	PS1	PS1 200 mm		
	Ys	UTS	El. (%)	Y/U
	Min	50.000	65.000	18,00
	Max	65.000		0,85
02771		58.435	72.500	28,02
02771		57.275	72.355	27,70

Customer ref :  
 000002 : ANA ANGELE

Klecker Roberto  
 Porteur de signature spéciale


<b>Sales Agent:</b> ArcelorMittal Int. North America 1 South Dearborn, 13th floor CHICAGO IL 60603 USA		<b>ArcelorMittal Belval &amp; Differdange</b>  Service Gestion Qualité 66, rue de Luxembourg L-4009 Esch/Alzette	
<b>Plant:</b> ArcelorMittal Belval & Differdange Site de Differdange L-4503 Differdange		<b>Certificate NrX 3008720</b> Delivery note number 3008720 from 25 April 2015	
Our reference : 1700020456 Your reference : 20773 24.03.2015 Plesa Anahuac Y Cias, S.A. de C.V.		Plesa Anahuac Y Cias, S.A. de C.V. Av. Valle de las Alamedas 66-O 54940 COL. S. FRANCISCO CHILPAN, TUL MEXICO	
<b>ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED</b>			
<b>Manufacturer's test certificate acc. to ASTM A 6</b>			

Ord.Item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars
000002	W 27 X 10 X 94	40' 12.192 mm	20,484 mt	02772 02773	8,535 mt 11,949 mt		5 7


Heat nr	Heat analysis (%)														
	C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	CEV	Sn	Nb+V
	<b>Min</b>	<b>0,50</b>		<b>0,10</b>											
	<b>Max</b>	<b>0,23</b>	<b>1,60</b>	<b>0,035</b>	<b>0,045</b>	<b>0,40</b>	<b>0,60</b>	<b>0,45</b>	<b>0,35</b>	<b>0,150</b>	<b>0,050</b>	<b>0,150</b>	<b>0,45</b>	<b>0,150</b>	<b>0,150</b>
02772		0,08	1,16	0,025	0,024	0,18	0,009	0,20	0,11	0,16	0,039	0,001	0,040	0,34	0,02 0,040
02773		0,09	1,19	0,021	0,023	0,19	0,009	0,20	0,10	0,11	0,039	0,001	0,030	0,34	0,02 0,040

Heat nr	Tensile test			
	PSI	PSI 200 mm		
	Ys	UTS	El. (%)	Y/U
	<b>Min</b>	<b>50.000</b>	<b>65.000</b>	<b>18,00</b>
	<b>Max</b>	<b>65.000</b>		<b>0,85</b>
02772		56.260	69.600	27,73 0,81
02772		56.840	70.325	28,01 0,81
02773		56.985	71.920	28,17 0,79
02773		56.840	70.470	27,43 0,81

Customer ref :  
000002 : ANA ANGELE

Klecker Roberto  
Porteur de signature spéciale  


**Sales Agent:**  
 ArcelorMittal Int. North America  
 1 South Dearborn, 13th floor  
 CHICAGO IL 60603  
 USA

**ArcelorMittal Belval & Differdange**   
 Service Gestion Qualité  
 66, rue de Luxembourg  
 L-4009 Esch/Alzette

**Plant:**  
 ArcelorMittal Belval & Differdange  
 Site de Differdange  
 L-4503 Differdange

**Certificate NrX 3007643**  
 Delivery note number 3007643 from 24 April 2015

Our reference : 1700020456  
 Your reference : 20773  
 24.03.2015  
 Plesa Anahuac Y Cias, S.A. de C.V.

Plesa Anahuac Y Cias, S.A. de C.V.  
 Av. Valle de las Alamedas 66-0  
 54940 COL. S. FRANCISCO CHILPAN, TUL  
 MEXICO

**ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED**


Manufacturer's test certificate acc. to ASTM A 6

Ord.item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars
000003	W 30 X 10,5 X 108	40' 12.192 mm	7,852 mt	12764	7,852 mt		4

Heat nr	Heat analysis (%)															
	C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	CEV	Sn	Nb+V	
	Min	0,50			0,10											
	Max	0,23	1,60	0,035	0,045	0,40	0,60	0,45	0,35	0,150	0,050	0,150	0,45		0,150	
12764		0,06	1,06	0,018	0,026	0,17	0,010	0,21	0,16	0,13	0,014	0,001	0,050	0,30	0,05	0,015


Heat nr	Tensile test				
	PSI	PSI	200 mm		
	Ys	UTS	El. (%)	Y/U	
	Min	50.000	65.000	18,00	
	Max	65.000		0,85	
12764		58.580	72.500	24,47	0,81
12764		59.160	73.225	24,72	0,81

Customer ref :  
 000003 : ANA ANGELE

Klecker Roberto  
 Porteur de signature spéciale  




**Sales Agent:**  
 ArcelorMittal Int. North America  
 1 South Dearborn, 13th floor  
 CHICAGO IL 60603  
 USA

**ArcelorMittal Belval & Differdange**   
 Service Gestion Qualité  
 66, rue de Luxembourg  
 L-4009 Esch/Alzette

**Plant:**  
 ArcelorMittal Belval & Differdange  
 Site de Differdange  
 L-4503 Differdange

**Certificate Nr X 3007648**  
 Delivery note number 3007648 from 24 April 2015

Our reference : 1700020456  
 Your reference : 20773  
 24.03.2015  
 Plesa Anahuac Y Cias, S.A. de C.V.

Plesa Anahuac Y Cias, S.A. de C.V.  
 Av. Valle de las Alamedas 66-O  
 54940 COL. S. FRANCISCO CHILPAN, TUL  
 MEXICO

**ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED**


Manufacturer's test certificate acc. to ASTM A 6

Ord.item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars
000003	W 30 X 10,5 X 108	40' 12.192 mm	19,630 mt	02771 12764	3,926 mt 15,704 mt		2 8


Heat nr	Heat analysis (%)															
	C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	CEV	Sn	Nb+V	
	<b>Min</b>	0,50			0,10											
	<b>Max</b>	0,23	1,60	0,035	0,045	0,40	0,60	0,45	0,35	0,150	0,050	0,150	0,45	0,150		
02771		0,08	1,18	0,023	0,016	0,18	0,010	0,21	0,11	0,13	0,041	0,001	0,030	0,34	0,02 0,042	
12764		0,06	1,06	0,018	0,026	0,17	0,010	0,21	0,16	0,13	0,014	0,001	0,050	0,30	0,05 0,015	

Heat nr	Tensile test				
	PSI	PSI 200 mm			
	Ys	UTS	El. (%)	Y/U	
	<b>Min</b>	50.000	65.000	18,00	
	<b>Max</b>	65.000	0,85		
02771		53.940	70.760	28,80	0,76
02771		57.420	70.035	27,58	0,82
12764		58.580	72.500	24,47	0,81
12764		59.160	73.225	24,72	0,81

Customer ref :  
 000003 : ANA ANGELE

Klecker Roberto  
 Porteur de signature spéciale  


**Sales Agent:**  
 ArcelorMittal Int. North America  
 1 South Dearborn, 13th floor  
 CHICAGO IL 60603  
 USA

**ArcelorMittal Belval & Differdange**   
 Service Gestion Qualité  
 66, rue de Luxembourg  
 L-4009 Esch/Alzette

**Client:**  
 ArcelorMittal Belval & Differdange  
 Site de Differdange  
 L-4503 Differdange

**Certificate NrX 3007651**  
 Delivery note number 3007651 from 24 April 2015

Our reference : 1700020456  
 Your reference : 20773  
 24.03.2015  
 Plesa Anahuac Y Cias, S.A. de C.V.

Plesa Anahuac Y Cias, S.A. de C.V.  
 Av. Valle de las Alamedas 66-0  
 54940 COL. S. FRANCISCO CHILPAN, TUL  
 MEXICO

**ASTM A992 - ASTM A572 GR50 FINE GRAIN SILICON KILLED**

Manufacturer's test certificate acc. to ASTM A 6

Ord.item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars
000003	W 30 X 10,5 X 108	40' 12.192 mm	1,963 mt	02771	1,963 mt		1

Heat nr	Heat analysis (%)														
	C	Mn	P	S	Si	N	Cu	Ni	Cr	V	Nb	Mo	CEV	Sn	Nb+V
	Min	0,50			0,10										
	Max	0,23	1,60	0,035	0,045	0,40	0,60	0,45	0,35	0,150	0,050	0,150	0,45	0,150	
02771		0,08	1,18	0,023	0,016	0,18	0,010	0,21	0,11	0,13	0,041	0,001	0,030	0,34	0,02 0,042

Heat nr	Tensile test				
	PSI	PSI 200 mm			
	Ys	UTS	El. (%)	Y/U	
	Min	50.000	65.000	18,00	
	Max	65.000		0,85	
02771		53.940	70.760	28,80	0,76
02771		57.420	70.035	27,58	0,82

Customer ref :  
 000003 : ANA ANGELE

Klecker Roberto  
 Porteur de signature spéciale  
