

ArcelorMittal Int. North America
 1 South Dearborn, 13th floor
 CHICAGO IL 60603
 USA

ArcelorMittal Belval & Differdange

ArcelorMittal

Service Gestion Qualité
 66, rue de Luxembourg
 L-4009 Esch/Aizette

Plant:

ArcelorMittal Belval & Differdange
 Site de Differdange
 L-4503 Differdange

Certificate Nr X 1663914

Delivery note number 1663914 from 26 November 2009

Our reference : 1700009774

Your reference : MEZCLA-FB-Q4
 23.10.2009

Ferre Barniedo, S.A. de C.V.

Ferre Barniedo, S.A. de C.V.
 Av. Revolucion #81
 Edo. de Mexico
 55000 SAN CRISTOBAL ECATEPEC, C.P.
 MEXIQUE

ASTM A992 - ASTM A572/01 GR50 FINE GRAIN SILICON
 KILLED

Manufacturer's test certificate acc. to ASTM A 6


41556

Ord.item	Product	Length	Weight	Heat nr	Weight	Bund.	Bars
000001	W 10 X 10 X 88	40' 12.192 mt	1,597 mt	85295	1,597 mt		1

Heat nr	Heat analysis (%)															
	C	Mn	P	S	Si	N	Al	Cr	V	Nb	Mo	CEV	Sn	Nb+V		
	Min	0,50			0,30											
	Max	0,23	1,60	0,035	0,40	0,40		0,60	0,15	0,55	0,150	0,050	0,150	0,45	0,150	
85295		0,08	1,56	0,09	0,02	0,18	0,012	0,25	0,16	0,10	0,058	0,002	0,040	0,41	0,01	0,060

Heat nr	Tensile test			
	PSI	PSI 200 mm	YS	El. (%)
	Min	50.000	65.000	1,00
	Max	65.000		0,85
85295		61.045	77.430	23,77
85295		58.725	76.560	22,48

Klecker Roberto
 Porteur de signature spéciale



FERRE BARNIEDO, S.A. DE C.V.
 ESTE ORIGINAL CERTIFICADO DE NUESTROS ARCHIVOS
 AMPARA ORIGINAL DE NUESTROS ARCHIVOS
 TEL. 58-36-10-00 REMISION NUESTROS ARCHIVOS
 ventas@ferrebarniedo.com.mx