

CIA. SIDERURGICA DE CALIFORNIA, S.A. DE C.V.

MATRIZ:

PLANTA GUADALAJARA

SUCURSAL:

AV. LAZARO CARDENAS No. 601

EDIF. "A" 3° PISO

COLONIA LA NOGALERA

TEL.:(01-33) 36-69-57-57 FAX: 38-11-82-02

C.P. 44440 GUADALAJARA, JALISCO, MEXICO.

LOTES 1 Y 2 INT. "A" COLONIA COLORADO No. 4

DELEGACION CERRO PRIETO

TELS:(01-686) 5-62-89-89 Y 58 FAX: 5-62-02-91

APDO. POSTAL 9-12 Y 9-14 MEXICALI

P.O.BOX 872-197 CALEXICO, CA. 92232

C.P. 21030 MEXICALI, B.C., MEXICO.

Certificado de Calidad

Quality Certificate

No REMISION
PACKING LIST No.

32520

FECHA
DATE

20/10/2005

HORA
TIME

15:37:50

No. CLIENTE
CUSTOMER No.

28657

ALMACEN
BRANCH

41827

R55370001

SOLD TO:
VENDIDO A:

PLESA ANAHUAC Y CIAS, S.A. DE C.V.

AV. VALLE DE LAS ALAMEDAS N.66-O
COL. SAN FRANCISCO CHILPAN
TULTITLAN EM CP:54940

MEX
RFC:PAC-040303-UY6

ENVIADO A:
SHIP TO:

PLESA ANAHUAC Y CIAS, S.A. DE C.V.
AV. VALLE DE LAS ALAMEDAS N.66-O

COL. SAN FRANCISCO CHILPAN
TULTITLAN EM CP:54940

MEX
RFC:PAC-040303-UY6

CONSIGNAR A:
C. BROKER:

TRANSPORTE
SHIP VIA

9830

Transportista Dummy Terrestre

No. GUIA
SHIPMENT No.

1741

No. PLACAS
LOC. PLATES

740 CM3

O/E
?

E

USUARIO
USER

AGONZALEZ

ANALISIS QUIMICOS/CHEMICAL ANALYSIS

COLADA	HEAT	Grado de Acero	%P	%S	%Sn	%C	%Cu	%Mo	%Si	%Ni	%Cr	%V	%Mn	%Nb	%Ti	C.Es	I.G.
362239	ASTM A36		.008	.035	.013	.220	.340	.052	.260	.260	.150	.003	.840	.001	.001		

ANALISIS MECANICOS Y FISICOS/MECHANICAL AND PHYSICAL PROPERTIES

COLADA	Norma de Fabricacion	Lim.Elast.	Esf.Max.	Elong.	Dureza	Estructura	Inclusiones	Tamaño Grano	Descarbur.	Doblez	Rec/Oval
HEAT	Product Especification	Yield Strength	Tensile Strength	(%)	Hardness	Estructure	Cleaness	Grain Size			
362239	ASTM A6/A 6M-94a	56,540	78,998	27							


COLADA
HEAT

Producto
Item

Atados por Colada
Bundles by Heat

362239 VIGA 6 A36 152.4MM

TFE02037 TFE02038 TFE02039



ASEGURAMIENTO DE CALIDAD